



Preparation of Nano Titanium Dioxide Using the Sol-Gel Method to Use in Friendly Environment Coatings

¹Abeer Abd Saleh*, ²Quraish Abbas, ³Seenaa Ibraheim, ⁴Ibrahim Muhammed, ¹Mayes Sameer Hameed, ¹Rukiya Abd Alsahb Lafta, ¹Sarah Gameel Dawood, ³Ban Mazan

¹National Center for Packing and Packaging/ Corporation of Research and Industrial Development – Iraq

²Chemical and Petrochemical Research Center/ Corporation of Research and Industrial Development – Iraq

³Department of Physics, College of Science, University of Baghdad – Iraq

⁴State Company for Mining Industries, Ministry of Industry and Minerals – Iraq

Article information

Article history:

Received: July, 30, 2021

Accepted: August, 20, 2021

Available online: October, 20, 2021

Keywords:

Local paint,
Sol-gel,
TiO₂

*Corresponding Author:

Abeer Abd Saleh
zoozaphysics3@gmail.com

DOI:

<https://doi.org/10.53523/ijoirVol8I2ID60>

Abstract

In this research, preparation of titanium dioxide nanomaterial (TiO₂) using sol-gel method was achieved. 2.5 g weight of the titanium dioxide nanoparticles were added to the local paint using the casting method. Thin films were prepared by drop casting the paint onto the surface of pre-prepared samples, then several tests were carried out including adhesion test, hardness test (Shore B), brightness and whiteness, friction test, contact angle, and antibacterial activity. The nanomaterial at a percentage of 12% showed the best results when it was added to the paint. These results include adhesion strength, hardness strength, and exposing to weather conditions of temperature, and humidity. The adhesive strength increased when adding the nanomaterial from 112 to 139 before exposure to the weather and from 58 to 108 after exposure. The hardness also increased from 77.9 to 86.5 before exposure to the surrounding environment and from 94.2 to 96.8 after exposure. In addition, the paint with TiO₂ nanoparticles exhibited antibacterial activity against two types of bacteria *Escherichia coli* (*E. coli*), *staphylococcus aureus* (*S. aureus*) and *antifungal candida*. Paint with TiO₂ nanoparticles is more efficient as antibacterial agents with *E. coli* as compared with *S. aureus* and *candida*.


1. Introduction

Titanium dioxide (TiO₂) has numerous applications that are friendly to the environment, such as: paint, sunscreen, and food colouring. TiO₂ under UV illumination displays photograph synergist movement that empowers the oxidative obliteration of a wide scope of natural mixtures and organic species, causing self-cleaning impact. In extra, TiO₂ uncovered under UV displays photograph chemically prompted super hydrophilicity that changes the hydrophobic character of the surface over to hydrophilic and structures the uniform water film, which forestalls the attachment of inorganic or natural parts on its surface, tidiness[1]. This is credited to its electronic and optical

properties, minimal effort, non-poisonousness, high solidness, and high proficiency in the debasement of natural toxins in air and water. TiO₂ exhibits wide band gap (3.0 eV for rutile and 3.2 eV for anatase) which restricts its light absorption to the only ultraviolet region. Consequently, pure TiO₂ works as a photo-catalytic material under UV light (4–5% of solar light), but it has a very weak photo-catalytic activity in visible light (45% of solar spectrum). This restricts the applications of TiO₂ as a photo-catalyst and in the solar light collecting [2] [3]. Transparent SiO₂-TiO₂ films on glass could form the basis for self-cleaning of indoor windows, lamps or windshields. To maximize the utilization of titanium dioxide for practical industrial applications, it is necessary to develop TiO₂ film type, especially for photo-catalytic applications. Titanium dioxide forms three diverse translucent polymorphic structures: rutile (tetragonal), anatase (tetragonal) and brookite (orthorhombic). Among these, the anatase stage as a rule shows the best photograph synergist conduct, while the rutile stage is the steadiest stage. Photograph impetuses might be utilized as a suspension in a watery arrangement or it could be immobilized on to a supporting substrate [4]. Self-cleaning surface is conceivably a valuable expansion for some business items because of financial, stylish, and natural reasons. Self-cleaning materials that can be cleaned by just being flushed with water can be conceivably applied in numerous spaces [5]. Finally, the preparation of nanoscale materials in the manner of sol-gel and study conduct the application tests, its impact on the environment in terms of disposal of dust and various environmental pollutants using several measurements or tests including measurement of the angle of contact, antibacterial (gram-positive and negative), mechanical test when adding to the local paint etc.

2. Experimental Procedure

Sol-gel technique is a wet synthetic cycle that permits a metal oxide to be delivered from naturally altered precursor materials at lower handling temperatures than a customarily made inorganic oxides [6]. The sol-gel method depends on inorganic polymerization responses. It incorporates four stages: hydrolysis, polycondensation, drying and warming disintegration. Hydrolysis of the antecedents of the metal or non-metal alkoxides takes place with water or alcohols [7].



where R = alkyl bunch. In addition to water and alcohol, an acid or a base also helps in the hydrolysis of the precursor. After condensation of the solution to a gel, the solvent is removed [7].



The weight ratio of chemical materials to prepare the local paint is shown in Table (1).

Table (1). The Weight ratio of chemical materials used in dye [8].

Material	Weight ratio (%)
Alkyd resin	55
Titanium dioxide	12
Calcium carbonate	12.5
Thickener material	3
Dilute material	14.6
Cobalt dryer	0.6
Lead dryer	0.4
Calcium dryer	1.2
Dilute grinding assistant	0.5
Anti-flake	0.2

Preparation of Nano TiO₂ Solution

A 1 ml of concentrated hydrochloric acid was added to 15 ml of titanium trichloride (TiCl₃). 250 ml of distilled water then gradually added to the previous solution followed by adding 150 ml of ethyl alcohol. The formed solution was then stirred continuously at 70°C for 5 hours. Afterward, 60 ml of ammonium hydroxide solution added while stirring is continued. The resulted solution was left for 24 hours to complete the reaction quietly.

Preparation of Local Paint

The alkyd resin is weighed, then added the dilute grinding assistant and mixed well. The pigment is added to the alkyd resin, so it will be nano- or microparticles. Calcium carbonate and thickener are added respectively, to the mixture and mixed well after each addition. The mixture was left one day to moisturize the solids well with alkyd resin. On the second day, the solvents, dryers, and anti-flakes are added to the mixture and mixed them well after each addition. The TiO₂ mixture with a percentage of 12% was added to the dye and mixed well until it became homogeneous by the magnetic mixer. And then the composite materials were mixed with a local paint, and poured on the plates made of iron with dimensions of 10 cm × 5 cm and left for a whole day till the dye dried up. Several assays were made including the hardness, paste, and color degree examination such as whiteness, brightness, and exposure to weather conditions (heat and moisture) to accelerate weather conditions impacts.

3. Results and Discussion

Surface Topography

Figure (1) shows the atomic force microscope (AFM) test of the nanometres titanium oxide powder obtained by the (sol-gel) process thin film prepared from TiO₂ by spraying the material on a glass base, with a thickness of 56 nm, an area of (1000 × 1000) nm square, and the average roughness is about 6.76 nm. The record was previously taken from the published research [9].




Figure (1). AFM examination of the thin film TiO₂.

Adhesion Pull-Off

The bond strength of nano TiO₂ paint is significantly higher than micro TiO₂ paint for both cases; before exposure to weather conditions and after exposure to weather conditions (ultraviolet, visible, and moisture). The quality of interface and the strength of the adhesion at the interface determine the load transfer between the matrix and the nano fillers [10]. Table (3) shows that TiO₂ nanoparticles content can improve adhesion. This positive result can be attributed to the reinforcement provided by the good dispersion and high compatibility between the paint and the nano TiO₂. The importance of adhesion is the ability of a coating to resist removal from the surface to which

it is applied [11]. Such adhesion can be between substrate and coating or between a primer coating and a top coating.

Table (3). Adhesion strength of the paint before and after exposure to weather conditions.

Adhesion before exposure to weather conditions (MPa)	Adhesion after exposure to weather conditions (MPa)
Paint with micro TiO ₂ = 112	Paint with micro TiO ₂ = 58
Paint with nanoTiO ₂ = 139	Paint with nanoTiO ₂ = 108

Hardness Test (Shore B)

Coating hardness is the ability to resist permanent indentation, scratching, cutting, and penetration by a hard object [11]. Different methods of evaluating hardness yield different results, because they measure different qualities of the material. Figure (2) shows the improvement in hardness of the paint with nano TiO₂. Hardness results show an excellent interaction between TiO₂ nanoparticles and the paint matrix. Moreover, the good dispersion of the particles, leads to an increase in the surface area of the filler. Mechanical properties of the nano composites can be altered by various factor: properties of the matrix, filler particles size and morphology, particles loading and distribution, interfacial adhesion between filler particles and matrix [12]. Figure (3) shows that hardness values increase for both paints (nano and micro) after exposure to weather conditions.




Figure (2). A histogram of Shore hardness for micro and nano TiO₂ paints before exposure to weather.




Figure (3). A histogram of Shore hardness for micro and nano TiO₂ paints after exposure to weather.

Friction Test

The samples of micro paint failed before and after exposure to weather conditions and after the 48 cycles. While the nano paint sample succeeded after exposure to weather conditions. Although, this sample was failed before exposure to weather conditions after 48 cycles.

Brightness and Whiteness

The brightness of the micro paint was faded after exposure to the weather conditions, whereas the nano paint exhibited a sharper brightness after weather conditions exposure as shown in Table (4). TiO_2 is the most widely used white pigment because of its brightness and very high refractive index [13]. Table (5) tabulates the brightness results, where one can see that micro painted samples exhibit a decrease in whiteness after weather exposure compared to its value before the exposure. On the other hand, nano painted samples demonstrate an increase in whiteness after weather exposure.

Table (4). Brightness of paint with micro and nano TiO_2 .

Samples	Before exposure to weather conditions	After exposure to weather conditions
Paint with micro	175.96	169.56
Paint with nano	165.86	176.38

Table (5). Whiteness of paint with micro and nano TiO_2

Samples	Before exposure to weather conditions	After exposure to weather conditions
Paint with micro	141.32	128.03
Paint with nano	130.76	139.38

Contact Angle

Contact angle measurement is shown in Figure (4). When the contact angle increases to more than 90° , the surface is considered a hydrophobic, but when the surface contact angle is less than 90° , the surface is hydrophilic. In the present work, with ultraviolet radiation, sun, moisture and TiO_2 nanoparticles, the surface contact angle converts from hydrophilic to super hydrophilic for TiO_2 nano and micro paints. Exposure to weather conditions results in a decrease in contact angle for both micro paint and nano paint surfaces which creates a hydrophilic surface. Hydrophilicity depends on both the surface roughness and the chemical composition [14].




Figure (4). Contact angle: (a) paint with micro TiO₂ before exposure to weather condition (b), paint with micro TiO₂ after exposure to weather condition, (c) paint with nano TiO₂ before exposure to weather condition, and (d) paint with nano TiO₂ after exposure to weather condition.

The paint with TiO₂ nanoparticles was investigated as antibacterial in two different bacteria: *Escherichia coli* (*E. coli*), *Staphylococcus aureus* (*S. aureus*), and fungal *Candida*, as well. Paint with TiO₂ nanoparticles showed greater antibacterial activity. The exact mechanisms of the antibacterial action have not yet been clearly identified. TiO₂ nanoparticles have bactericidal effects on both Gram-positive (*S. aureus*) and Gram-negative (*E. coli*) bacteria. The antibacterial activity of TiO₂ nanoparticles depends on the surface area and concentration, while the crystalline structure and particle shape have little effect. Zone of inhibition values determined nanocomposites is shown in Table (6) and Figure (5). TiO₂ nanoparticles pronounced significant growth inhibitory effect against both bacteria due to their large surface area by their nanosize. However, TiO₂ nanoparticles superior antibacterial activity against *E. coli* bacteria than with *S. aureus* bacteria which are clearly visualized in the antibacterial photographs [15].

Table (6). Zone of inhibition (mm) of paint with TiO₂ Nano particle.

Samples	<i>S. aureus</i>	<i>E. coli</i>	<i>Candida</i>
Area 1	17	18	14
Area 2	17	18	14
Area 3	17	18	14




Figure (5). Antibacterial and antifungal activity of Nano paint.

4. Conclusions

The TiO₂ nanoparticles prepared by chemical method (sol-gel) gave good results. When adding it to the local dye when conducting several dye tests, including adhesive and hardness and contact angle. Examined the dye before it was exposed to weather conditions and after exposure in a micro-form once and in a nano, in the other, the adhesion strength and hardness increased with adding the nanomaterial.

References

- [1] W. Sangchay, "The Self-cleaning and Photocatalytic Properties of TiO₂ Doped with SnO₂ Thin Films Preparation by Sol-gel Method," *Energy Procedia*, vol. 89, pp. 170–176, 2016.
- [2] S. M. Reda, M. Khairy, and M. A. Mousa, "Photocatalytic activity of nitrogen and copper doped TiO₂ nanoparticles prepared by microwave-assisted sol-gel process," *Arab. J. Chem.*, vol. 13, no. 1, pp. 86–95, 2020.
- [3] S. Lourduraj and R. V. Williams, "Effect of molarity on sol-gel routed nano TiO₂ thin films," *J. Adv. Dielectr.*, vol. 7, no. 6, pp. 1–7, 2017.
- [4] A. Shokuhfar, M. Alzamani, E. Eghdam, M. Karimi, and S. Mastali, "SiO₂-TiO₂ Nanostructure Films on Windshields Prepared by Sol-Gel Dip-Coating Technique for Self-Cleaning and Photocatalytic Applications," *Nanosci. Nanotechnol.*, vol. 2, no. 1, pp. 16–21, 2012.
- [5] M. Farahmandjou, "Study of Nano SiO₂/TiO₂ Superhydrophobic Self-Cleaning Surface Produced by," *Aust. J. Basic Appl. Sci.*, no. April 2013, pp. 4–8, 2014.
- [6] S. Ibrahim, "Synthesis and characterization of the PMMA / SiO₂ hybrids by sol-gel method," *Chem. Mater. Res.*, vol. 6, no. 1, pp. 52–61, 2014.
- [7] S. Gupta and M. Tripathi, "A review on the synthesis of TiO₂ nanoparticles by solution route," *Open Chem.*, vol. 10, no. 2, pp. 279–294, 2012.
- [8] A. A. Salih, A. J. Haider, and A. Nazar, "Preparation and Characterizations of Nanomaterial by Pulsed Laser Ablation in Liquid (PLAIL) as Friendly Environment Paint," *J. Phys. Conf. Ser.*, vol. 1795, no. 1, pp. 0–11, 2021.
- [9] Q. A. Kadhum, I. Development, and K. Sahan, "Preparation of Nano-Titanium Dioxide and Manufacturing Nano Thin Film," *J. Iraqi Ind. Res.*, vol. 1, no. 1, pp. 25–31, 2014.
- [10] N. Ameer and S. Ibreheim Hussein, "Enhanced thermal expansion, mechanical properties, and adhesion analysis of epoxy / ZrO₂ nano composites," *J. Phys. Conf. Ser.*, vol. 1279, no. 1, 2019.
- [11] "Paint and Coating Testing Manual, (Gradner-Sward Handbook, 14th Edition) edited by Dr. Joseph V. Koleske, American Society of Testing and Materials, Philadelphia, PA, 1995, pp. 950; hardcover, \$220 list; \$198 ASTM members," *Color Res. Appl.*, vol. 20, no. 4, p. 270, Aug. 1995.
- [12] H. Song, J. Liu, F. Xue, and F. Cheng, "Study of inorganic powders used for preparation of waterproof coating to coal mine roadways," *Polimery*, vol. 61, pp. 844–849, 2016.
- [13] R. Sharafudeen, "The manufacturing process parameters affecting color and brightness of TiO₂ pigment," *Int. J. Ind. Chem.*, vol. 3, no. 1, pp. 1–7, 2012.
- [14] E. Pakdel, W. A. Daoud, and X. Wang, "Self-cleaning and superhydrophilic wool by TiO₂/SiO₂ nanocomposite," *Appl. Surf. Sci.*, vol. 275, pp. 397–402, 2013.
- [15] A. J. Haider, Z. N. Jameel, and I. H. M. Al-Hussaini, "Review on: Titanium Dioxide Applications," *Energy Procedia*, vol. 157, pp. 17–29, 2019.