

Available online at http://qu.edu.iq/journalsc/index.php/JOPS

Al-Qadisiyah Journal Of Pure Science (QJPS)

Vol. 24, No. 4, pp. 56-60,Year 2019

Study of the structural and optical properties of ZnO and ZnO/Fe2O3 thin films grown by chemical bath deposition .

Qasim Chfat Abdulridha and Hussein Ali Noor

Qadisiyah, Iraq, qaseemjafat@gmail.com, ah2008@mail.ru, Physics Department, College of Education, University of

Qadisiyah

ABSTRACT:

ZnO andZnO/Fe2O3 composite thin films were prepared by chemical bath deposition technique with thicknesses (150 ± 20) nm. X-ray diffraction analysis showed that pure and composite films polycrystalline in nature with Hexagonal structure and the preferred orientation along (100) plane. The calculated crystallite size of the deposited films are found to be decreases with composite films. Thesurface morphology of the films was studied by Atomic force microscope, the surface morphology of pure and ZnO composite films are homogeneous distribution. The optical properties of all deposited ZnO and composite films contained study of transmittance and absorbance spectral in the range of wave length (300- 1100)nm, Transmittance increased with composite films, The value of the optical energy gap (Eg) were found decrease with composite films due to the effective electron/holes at the inter faces of ZnO/Fe2O3.

KEYWORDS: ZnO/Fe2O3 Thin films, composite, Structural and optical properties, (CBD).

1. INTRODUCTION

Nanocrystalline materials, among them ZnO semiconductor nanocrystals doped with 3d metal ions (Fe, Ni, Co, Mn), received considerable attention as potential components of future nanotechnology. Thin films of ZnO have been studied as the active material in the development of thin film transistors due to their n-type semiconductor characteristic and excellent thermal stability, and can be well-oriented crystalline in various substrates. (S.A. Wolf,et,al,2001), (Masuda,S,et,al,2003). Most prominent crystalline structure of ZnO is wurtzite type, although, it also exists in the cubic zinc blende and Hexagonal structures.In wurtzite type, each Zn ion is surrounded by a tetragonal coordination. This give rise to polar symmetry along the hexagonal axis, which is responsible for a number of properties of ZnO (Ramamoorthy, K ,et, al , 2004). Thin films have been widely used in transparent electrodes, surface acoustic wave devices, field effect transistors and display devices. ZnO is a useful, economical and environmental semiconductor material because of its typical properties such as a wide direct band gap (3.3 eV) (Y. Yan, et, al.,2009),(Pankove, J. I. (1971).

2. Experimental part The glass substrates of 75x25x1 mm dimensions were

washed with Laboratory detergent and rinsed with distilled water in abundance water and acetone for several times in ultrasonically cleaned and finally dried in air. Thin film of ZnO and composite ZnO/Fe2O3 nanostructure were grown glass substrate by using chemical bath deposition(CBD) technique.ZnO films were prepared using aqueous solutions of zinc (II) chloride (ZnCl₂) 1M in de-ionized water to the volume of 100ml under magnetic stirring about 5 minutes and 0.1 M Iron chloride solution was prepared in 100 ml of di-ionized water using magnetic stirrer for 5 minute and NaOH 3M in de-ionized water to the volume of 50 ml under magnetic stirring about 5 minutes after solution (NaOH) was added 10ml drop wise into the mixed solution. The measured pH value at the step varied between 9.8 and 11. Prior to the deposition, the beaker containing the deposition solution was placed in the water bath at 80 °C for about 5 minutes to stabilize the temperature of the solution, then the beaker was kept in the water bath. At the end of the deposition time (1 hour), the slides were taken out, rinsed with distilled water and allowed to dry with warm air. Samples were Characterized using with X-ray diffraction type (SHIMADZU Japan XRD 6000) to identify the crystal Al-Qadisiyah Journal Of Pure Science (QJPS)

Vol. 24, No. 4, pp. 56-60, Year 2019

structure of the prepared films, The surface morphology was analyzed by Atomic Force Microscope (AFM) device type (SPM AA3000 /Angstrom Advanced Inc.),Optical spectrums of the films were recorded by UV-Visible Shimadzu 1800 spectra photometer

3. Results and Discussion

3.1 Structural properties

The crystallite size (D) was calculated using Scherrer's formula [11].

$$D = \frac{k\lambda}{B\cos\theta} \tag{1}$$

Where K: is Scherer constant and that is equal to $[2(\ln 2/\pi)1/2=0.94]$ λ : wavelength, and B: full width at half In radian.

The absorption $\operatorname{coefficient}(\alpha)$ determine according to the following equation [12].

$$\alpha = 2.303 \frac{A}{t} \tag{2}$$

Where t is film thickness, A is the film absorption .

The optical band $gapE_g^{opt}$ was calculated By Tauc relation[12].

 $\alpha h v = B (h v - E_g^{opt})^r$ (3) Where h v is photon energy, B constant depends on the nature of the material, and r is the value depends on the nature of the transition.

The Study of ZnO and composite ZnO/Fe2O3 thin films were analyzed for their structural properties by recording Xray diffraction pattern, Fig.(1) shows the XRD pattern of ZnO films which was deposited on glass substrates at bath temperature 353 K for deposition time 1 hr. The peaks from the diffraction patterns were found to be characteristic to ZnO and composite ZnO/Fe2O3 thin films compared with standard ICD card No. 00-036-1451. All films exhibit peaks related to polycrystalline Hexagonal structure with preferential orientation of (100)plane (LinhuaXu,et,al,2010),(Sreeja,et,al,2010) . As shown in table1.



Fig1: XRD pattern of deposited ZnO and composite ZnO/Fe2O3 .

Figure (2a,b). presents AFM two dimensions (6.19 μ m ×6.19 μ m) (2D, 3D) images From this images by Atomic force microscope, the surface morphology of pure and ZnO composite films are non-homogeneous distribution (**Das**, et al.,2007).



Fig. 2. AFM images (2D , 3D) of a: ZnO b: ZnO/Fe2O3.

ISSN 2411-3514 ONLINE ISSN 1997-2490 PRINTED QJPS. Journal Of Pure Science

Al-Qadisiyah Journal Of Pure Science (QJPS)

Vol. 24, No. 4, pp. 56 -60, Year 2019

Material	ZnO	ZnO/Fe ₂ O ₃
2 O (deg)	31.6	32.2
d(Å) Observed	2.82	2.77
d(Å) Standard	2.81	2.81
FWHM (deg)	0.1998	0.23610
(hkl)	(100)	(100)
Averagecrystalline Size (nm)	43.18	36.59
4.2 Ontical Properties		

ZnO/Fe2O3 .

Tab1.1. XRD result of deposited ZnO and composite

The optical transmittance spectra of ZnO and composite ZnO/Fe2O3 thin films within the wavelengths of the range from (300 – 1100) nm. Fig3a. Shows the transmittance as a function of the wavelength of ZnO and composite ZnO/Fe2O3 thin films. where it can be observed an increase in transmittance by increasing the wavelength. It was also observed that the transmittance increasing by composite ZnO/Fe2O3 thin films . Fig3b. Shows that the absorbance as a function of the wavelength of ZnO and composite ZnO/Fe2O3 thin films . Fig3b. Shows that the absorbance as a function of the wavelength of ZnO and composite ZnO/Fe2O3 films, where observe the absorption values decrease by increasing the wavelength, it can be seen decreasing with composite ,This spectrum reveals

that ZnO/Fe2O3 film have low absorbanceBecause Iron effect on crystalline composition of material (Xu, L,et,al,2010) , (Sreeja,et,al,2010).



Fig3. a. optical transmittance curves of ZnO and composite ZnO/Fe2O3



Fig3. b. the optical absorption curves of ZnO and composite ZnO/Fe2O3.

Fig.4 the absorption coefficient as a function of the energy photon $(h\sigma)$, it can be seen that the films have a high absorption coefficient (α >104cm-1) which indicates direct electronic transitions.



Fig4. absorption coefficient of ZnO and composite ZnO/Fe2O3 thin films.

The optical energy gap has obtained from intercept of the extrapolated linear part of the curve with the photon energy axis (hv) at $(\alpha hv)^r = 0$. The linear nature of the plots at the absorption edge confirmed that all deposited films are a semiconductor with direct band gap. These results showed that E_g^{opt} is (3, 2.8) eV of ZnO and composite ZnO/Fe2O3 respectively,and composite have low ZnO/Fe2O3 Because the conduction band of ZnO lies above Fe2O3, which

ISSN 2411-3514 ONLINE ISSN 1997-2490 PRINTED Available online at http://qu.edu.iq/journalsc/index.php/JOPS



Al-Qadisiyah Journal Of Pure Science (QJPS) ISSN 2411-3514 ONLINE ISSN 1997-2490 PRINTED

Vol. 24, No. 4, pp. 56-60, Year 2019

Reduce the energy gap(Choudhury, N,et,al,2009), (Pierson, H. O.,1999).



Fig5. The optical energy gap of ZnO and composite ZnO/Fe2O3 thin films

5. Conclusions

Chemical bath deposition method is an easy and inexpensive to prepare ZnO thin films. XRD studies of ZnO and composite ZnO/Fe2O3 films indicated the formation of nanocrystalline with polycrystalline hexagonal phase, and the average crystallite size are equal to (43.18, 36.59) nm respectively. thin films by Atomic force microscope , the surface morphology of pure and ZnO composite films are homogeneous distribution. The high optical transmittance in wavelength region(T > 500 nm), its advantageous features of ZnO thin films that works as filters, and antireflection coating to improve solar cell efficiency, It was also observed that the transmittance increasing by composite ZnO/Fe2O3 thin films. The optical gap The films have allowed direct transition and the optical energy gap values (3, 2.8) eV of ZnO and composite ZnO/Fe2O3 respectively and composite have low ZnO/Fe2O3 Because the conduction band(CB) of ZnO lies above Fe2O3which reduce the energy gap(Pierson, H. 0.,1999).

References

- Pankove, J. I. (1971). Optical processes in semiconductors Prentice-Hall. *New Jersey*, 92.
- Choudhury, N., & Sarma, B. K. (2009). Structural characterization of lead sulfide thin films by means of X-ray line profile analysis. *Bulletin of Materials Science*, 32(1), 43-47.
- Cullity, B. D., & Stock, S. R. (2001). *Elements of X-ray Diffraction* (Vol. 3, p. 15). New Jersey: Prentice hall.
- Das, S., &Chaudhuri, S. (2007). Mg2+ substitutions in ZnO– Al2O3 thin films and its effect on the optical absorption spectra of the nanocomposite. *Applied surface science*, 253(21), 8661-8668.
- Masuda, S., Kitamura, K., Okumura, Y., Miyatake, S., Tabata, H., & Kawai, T. (2003). Transparent thin film transistors using ZnO as an active channel layer and their electrical properties. *Journal of Applied Physics*, 93(3), 1624-1630.
- Pierson, H. O. (1999). Handbook of chemical vapor deposition: principles, technology and applications. William Andrew.
- Ramamoorthy, K., Arivanandhan, M., Sankaranarayanan, K., & Sanjeeviraja, C. (2004). Highly textured ZnO thin films: a novel economical preparation and approachment for optical devices, UV lasers and green LEDs. *Materials chemistry and physics*,85(2-3), 257-262.
- Sreeja, R., John, J., Aneesh, P. M., & Jayaraj, M. K. (2010). Linear and nonlinear optical properties of luminescent ZnO nanoparticles embedded in PMMA matrix. *Optics Communications*, 283(14), 2908-2913.

Available online at http://qu.edu.iq/journalsc/index.php/JOPS



Al-Qadisiyah Journal Of Pure Science (QJPS) ISSN 2411-3514 ONLINE ISSN 1997-2490 PRINTED

Vol. 24, No. 4, pp. 56 -60, Year 2019

- Wolf, S. A., Awschalom, D. D., Buhrman, R. A., Daughton,
 J. M., Von Molnar, S., Roukes, M. L., ... & Treger, D.
 M. (2001). Spintronics: a spin-based electronics vision for the future.*science*, 294(5546), 1488-1495.S.
- Xu, L., & Li, X. (2010). Influence of Fe-doping on the structural and optical properties of ZnO thin films prepared by sol–gel method. *Journal of Crystal Growth*, 312(6), 851-855.
- Yan, Y., Zhou, L., Zou, J., & Zhang, Y. (2009). Synthesis and growth discussion of novel ZnO nanotetrapods with pearl-necklace-shaped arms. *Applied Physics A*, 94(3), 559-565.