



وزارة التعليم العالي والبحث العلمي
جامعة ميسان
كلية التربية الأساسية

Ministry of Higher Education and Scientific
Research
University of Misan
College of Basic Education

Misan Journal for Academic Studies
Humanities, social and applied sciences

مجلة ميسان
للدراسات الأكاديمية
العلوم الانسانية والاجتماعية والتطبيقية

ISSN (Print) 1994-697X
(Online)-2706-722X

المجلد 24 العدد 53 اذار 2025

Mar 2025 Issue53 VOL24



مجلة ميسان للدراسات الاكاديمية

العلوم الإنسانية والاجتماعية والتطبيقية

كلية التربية الأساسية / جامعة ميسان / العراق

Misan Journal for Academic Studies

Humanities, social and applied sciences

College of Basic Education/University of Misan/Inq

ISSN (Print) 1994-697X (Online) 2706-722X

2025	اذار	العدد 53	المجلد 24
2025	Mar	Issue53	VOL24



OJS / PKP
www.misan-jas.com

IRAQI
Academic Scientific Journals



ORCID

OPEN ACCESS



 journal.m.academy@uomisan.edu.iq

رقم الابداع في دار الكتب والوثائق بغداد 1326 في 2009

الصفحة	فهرس البحوث	ت
14 - 1	Evaluation of anti-plaque and anti-inflammatory efficacies of mouth rinse containing green tea and <i>Salvadora Persica L.</i> in the management of dental biofilm-induced gingivitis Aliaa Saeed Salman Maha Abdul Azeez Ahmed	1
26 - 15	Evaluation of galectin-3 and peptidyl arginine deiminase-4 levels in saliva for periodontal health, gingivitis and periodontitis Yusur Ali Abdulrazzaq Alaa Omran Ali	2
37 - 27	EFFECT OF HYPOCHLOROUS ACID ON SURFACE ROUGHNESS AND WETTABILITY OF ZINC OXIDE EUOGENOL IMPRESSION PASTE Israa J.Taha Shorouq M. Abass	3
47 - 38	Annual groundwater recharge estimation in Nineveh plain, northern Iraq using Chloride Mass Balance (CMB) method Fatima AJ. Abdul Wahab Alaa M. Al-Abadi	4
61 - 48	A Theoretical Study for Excitation of Electrons Collides with Positive Nitrogen Ions Hawraa S. Kadhim Alaa A. Khalaf	5
72 - 62	Green synthesis of gold nanoparticles (AuNPs) using pathogenic bacteria <i>Acinetobacter baumannii</i> with evaluation their antibacterial activity Hawraa Khalaf Abbood Rashid Rahim Hateet	6
82 - 73	Structural, Optical and Gas Sensor Properties of Zinc Oxide Nanostructured thin films prepared by Chemical Spray Pyrolysis Ameer I. Khudadad Ezzulddin Abdoulsahib Eesee	7
91 - 83	Soft denture liner and its additives (A review of literature) Ibrahim Ali Al-Najati Ghasak Husham Jani	8
103 - 92	A Critical Discourse Analysis of the Language of Persuasion in Political Discourse Mohammed Hussein Hlail	9
116 - 104	A Comprehensive Review of Rice Husk Derived Silica As Nano Filler (A review of literature) Azza Walaaldeen Khairi Huda jaafar naser	10
125 - 117	Evaluation of Superoxide Dismutase and their association with Diabetic neruopathy and Heart disease in Iraq populations Zainab A. Salman	11
139 - 126	Schema Theory in Sarah Moss's "The Fell": A Cognitive Stylistic Study Salah R. Al-Saed Nazar Abdul Hafidh Abeid	12
149 - 140	Validation and Development of UV spectroscopy method for the Estimation of Diclofenac sodium in Bulk and dos protected mode interface Mohammed R . Abdul - Azeez	13
167 - 150	Using A Genetic Algorithm to Solve the Inventory Model with A Practical Application Ahmed Jamal Mohammed Al-Botani Faris Mahdi Alwan Al-Rubaie	14
180 - 168	Seasonal Variatins of Polychlorinted Biphenyls compounds in Water of Tigris River , Maysan Province / Iraq Halima Bahar Kazem and Salih Hassan Jazza	15

200 - 181	The Reasons Behind the Societal Reversal on the Governance of Amir al-Mumineen After the Prophet's Death (Peace (PBUH)) Through the Sermons of Lady Fatima al-Zahra (Peace Be Upon Her) Fatima Abd Saeed Al-Maliki	16
217 - 201	The place and its Implications in Adghat Madinah novel " Saja Jasim Mohammed Assistant Instuctor	17
233 - 218	The Level of Strategic Thinking Among School Principals in the Center of Misan Governorate from the Perspective of Their Teachers Multaka Nasser Jabbar	18
253 - 234	The reality of the practice of Arabic language teachers in the primary stage of reciprocal teaching from the perspective of the specialty supervisors Khadija Najm Abdel Qader Ramla Jabbar Kazem	19
274 - 254	Optimal storage model to sustain the operation of Baghdad stations Establish an Faris Mahdi Alwan Ahmed Ali Mohammed	20
284 - 275	Poetry on the tongue of the other, a media vision. The poetry of Abu Marwan al-Jaziri (396 AH) is an example Sabreen Khalaf Hussein	21
297 - 285	Saudi-Japanese relations1938-1973(historical study Ali Joudah Sabih Al-Maliki Faraged Dawood Salman Al-Shallal	22
313 - 298	Influences on Al-Asma'i's Critical Judgment (A Critical Study) Hussam Kadhim Atiyah	23
334 - 314	The Effect of Felder and Silverman's Model in the Achievement of Fifth High School Female Students and Their Lateral Thinking in Mathematics. Shaymaa Kareem Hassoon	24
344 – 335	Enzymatic Activity of Fungi Isolated From the Bases of Stems and Roots of Faba Bean Plants Infected with Root Rot Disease Asia N Kadim Ali A Kasim Ghassan Mahdi Daghir	25
364 - 345	Alternative Means for Resolving Disputes Arising from Trading in the Securities Market (A Comparative study) Saja Majed Daoowd	26



...

ISSN (Print) 1994-697X
ISSN (Online) 2706-722X


DOI:

<https://doi.org/10.5463/3/2333-024-053-008>

Received:22/12/2024

Accepted:13/2/2025

Published online:31/3/2025



Soft denture liner and its additives (A review of literature)

¹ Ibrahim Ali Al-Najati

² Ghasak Husham Jani

^{1,2} Department of Prosthodontics, College of Dentistry, University of Baghdad, / Baghdad, Iraq.

Ibrahim.Ali2401m@codental.uobaghdad.edu.iq

ORCHID ID - <https://orcid.org/0009-0008-1856-5022>

Abstract:

Soft liners are used with patients who cannot tolerate the hard acrylic base. It is used in complete and partial removable dentures to distribute functional loads homogeneously on the denture-bearing tissues to increase patient acceptance and relieve pain. These materials are recommended in cases of irregular bone resorption, bony undercuts, thin atrophic mucosa, immediate prosthesis, healing after implant placement, and for patients with bruxism and xerostomia.

However, the structure of the soft liner encourages the colonization of microorganisms, so the soft liner must be modified to overcome any possible infection that may occur during use, especially to prevent denture stomatitis, the most common disease associated with denture wearing caused by candida albicans.

Keywords: Soft liner. Antimicrobial Agents in soft liners. Essential oils activity. Nanoparticles as anti-fungal. Plant powder extract.

Introduction:

For many years, Polymethylmethacrylate has been extensively used and developed to construct acrylic denture bases (AlFuraiji *et al.*, 2024), which have good aesthetics, low toxicity, and a low water absorption rate (Noori *et al.*, 2023). However, the disadvantage is that it has inferior physical and mechanical properties and is susceptible to microbial colonization (Al-Shammari *et al.*, 2023). The use of nanoparticle fillers is one method that has successfully improved the characteristics of dental resin matrix (Al-Sammraie *et al.*, 2024).

Denture base relining:

A decisive part of the complete denture benefit is maintaining the adaptation of the denture base to the mucosa covering the residual ridges. Bonding between the denture base and relining materials is a very critical technique that may lead to microleakage at the denture base relining interface and then detachment of the relining material. The main indications of relining material are Poor adaptation of the denture to the supporting tissues, Sharp bony protuberances, Pressure points, Flabby and anthropic tissue, and Irregular, sharp, and bony ridges that cause painful mastication (Alfahdawi, 2018). whereas there are also contraindications of

relining, like Severe resorption of the residual ridge, Abused soft tissues, Temporomandibular joint disorder, the poor appearance of the existing dentures, problems in speech, and osseous undercuts are severe (Nallaswamy, 2017). The classification system for relining materials is based on consistency, including Tissue conditioning materials, Hard denture liners, and Soft lining materials. (McCabe & Walls, 2008)

Soft linings material:

Soft denture liners can be helpful for individuals who are unable to tolerate a traditional rigid denture foundation (Al-Rubaie & Al-Khafaji, 2024). A soft lining on the denture base will help to increase patient acceptance of the denture and relieve the pain, especially in cases where a thin, non-resilient mucosa covers the irregular mandible alveolar ridge (McCabe & Walls, 2008).

Soft liner materials are divided into two types according to composition: Silicone and acrylic, which are either heat-cured or auto-polymerized. According to duration, short and long-term soft liners. Short-term soft liners are normally applied for one month; intermediate liners retain elasticity from one to six months, and long-term permanent liners soft liners last more than one year (Dutta, 2022).

The soft lining material, to be ideal, must be Easy to manipulate with conventional laboratory equipment, Dimensional change during processing should be minimal, like that of the denture base materials, minimal water sorption and solubility, Resiliency should be high, Bond strongly to the denture base, sufficient tear resistance, easy to clean, non-toxic, tasteless and odorless, Its color should match that of the denture base material (Babu, 2019). The uses of soft lining material include Diagnostic relining, Impression material, If the patient suffers from mucosal discomfort and ulcerations, it can be used with immediate dentures, in the severely resorbed ridge and bony undercuts, improve the retention of the denture to the underlying tissue; soft-liners are used to reline the obturators for patients with congenital or acquired maxillofacial defects; patients suffering from xerostomia have increased soreness and discomfort, use to improve the adaptation of the denture after surgery, and use after-implant therapy to cover the implant site (Babu, 2019). The soft liner can also be used when the patient has financial constraints and is unable to pay for a new denture (Wadi & Khalaf, 2024).

Types of soft lining materials according to composition:

There are two types:

I. Plasticized acrylic resin-based soft liner:

Acrylic soft lining materials come in liquid and powder form, the liquid consisting of a higher MMA monomer (e.g., ethyl, n-butyl) and the powder consisting of a higher PMMA polymer. Also, the plasticizer is a phthalate (Chladek *et al.*, 2014).

Auto-polymerized acrylic soft-liner materials permit the clinician to do relining for removable dentures orally or extra orally. This method, when compared to the heat polymerized technique, is faster in use. However, producing liner materials with the optimum thickness is difficult when using the auto-polymerized technique. The maximum thickness for good shock absorption is around 2.5 to 3 mm. Two processes occur when acrylic resin-based denture liners are submerged in water: the plasticizers leaching out and other soluble materials in the water, whereas the polymer absorbs the

water. The plasticizer makes the polymer's glass transition temperature below mouth temperature, reducing the resilient material's modulus of elasticity to a satisfactory level (Chauhan *et al.*, 2021).

II. Silicone-based soft liners:

Silicone-based soft-liner materials resemble silicone impression materials in composition (dimethyl siloxane polymers). Polydimethyl siloxane is a viscous liquid that can cross-link to form a rubber material with strong elastic properties. There is no plasticizer required with this material to make a softening effect (Chauhan *et al.*, 2021).

This material lacks leachable plasticizers. Like silicone-based impression materials, these materials gain elastomeric properties with a silicone base and catalyzer mixture. The most important advantages of this material are ease of use and long-term softness. An adhesive is necessary since their connection to the acrylic denture base is not direct. A new generation of adhesives has much stronger connective properties but is still insufficient (Özkan, 2017). Finally, it can be used in case of complete dentures against natural dentition.

Antimicrobial Agents in soft liners:

Colonization of candida albicans is one of the serious flaws of soft-lining materials, which might eventually lead to denture stomatitis (Abdulwahhab & Jassim, 2018). Denture-induced stomatitis is an inflammatory disorder that affects the mucosa beneath removable dentures (Naser & Abdul-Ameer, 2023).

1-Essential oils added to soft liner:

In 2015, Tea tree oil was also known to have antifungal properties, especially against candida albicans, and the study found that tea tree oil aids in eradicating fluconazole-resistant candida in AIDs patients. A concentration of 0.25 percent of this oil can inhibit candida's multiplication by creating germ tubes. Tea tree oil can be used to soft liners and tissue conditioners to help with denture-induced stomatitis, suggesting a new oral candidiasis management method (Pachava *et al.*, 2015).

In 2017, seed oils were organically derived medicaments put into soft liner materials or tissue conditioners (800 µL) and have been shown to have potent anti-candida albicans efficacy (Muttagi & Subramanya, 2017).

In 2018, Virgin coconut oil was successfully added to the soft denture liner and acted as a potential antifungal agent against Candida albicans. The Addition of 1.5% and 2.5% of coconut oil used assesses the antifungal effect. 1.5% is better because it has the most beneficial effect against fungi, with good wettability and softness values and fewer adverse effects on the shear bond strength (Alamen & Naji, 2018)

In 2021, an investigation found that 20 v/v % curcumin oil added to a soft liner significantly reduced surface roughness compared to the untreated soft liner. Both empirical ratios of curcumin, 10 and 20% v/v, considerably improved the binding strength between the liner/base interface and its antifungal activity (Abdallah & Aref, 2021).

In 2021, a study evaluated the effect of Artemisia aerial oil and ethanol extracts on candida albicans growth and shear bond strength of soft denture liner.

The results showed that all oil concentrations inhibit candida albicans growth except 12.5 mg/ml, and the shear bond strength of the soft liner did not significantly differ from the control. In ethanol

extract, only 75 and 100 mg/ml concentrations inhibited candida albicans growth, and there were significant differences between all concentrations. At the same time, shear bond strength was increased, and there were significant differences with the control (Rashid, 2021).

In 2022, lemongrass essential oil was also investigated to assess antifungal properties, which can be regarded as a strong antifungal material, and incorporating it into a soft liner can successfully produce a soft lining material with antifungal activity against Candida albicans microorganisms. Significant improvement was made in most tested properties with concentrations of 2.5% and 5% v/v of lemongrass essential oil (Naser & Abdul-Ameer, 2022).

In late 2022, Litsea Cubeba Essential Oil was successfully added to the soft denture liner and acted as a potential antifungal agent against Candida albicans. The minimum inhibitory concentration of Litsea Cubeba Essential Oil against Candida albicans was 1.25% v/v (Songsang *et al.*, 2022).

So, it is unsurprising that herbal extracts have different antifungal and antibacterial properties. This is due to differences in the plants, their different extract methods and processing, the genetic structure of bacteria and fungi, and the same or different species of microorganisms (Petrović *et al.*, 2014).

2- Nano Particles added to soft liner:

In 2011 and 2021, silver nanoparticles were added to soft denture liners to assess their antifungal properties (Chladek *et al.*, 2011; Deng *et al.*, 2021). With long-term use, the acrylic soft liner containing silver nanoparticles synthesized in situ effectively controlled candida albicans adhesion (Deng *et al.*, 2021).

In 2017, Zirconium nanoparticles were successfully added to the soft denture liner and acted as a potential antifungal agent against Candida albicans. A highly notable decrease in Candida albicans colony in experimental groups of 1% and 1.5% of Zirconium nanoparticles in contrast with the control group. There was no inhibition zone around any specimen of the tested groups. However, there was a significant increase in the mean value of shear bonding strength after incorporating a 1.5% percentage into the soft liner (Yasser & Fatah, 2017).

In 2020, an investigation found that 1.5wt% and 2wt% of chitosan nanoparticles added to a soft liner showed a significant decrease in the number of Candida cells adhered to a soft liner compared to samples of the control group (Mohammed & Fatalla, 2020).

In 2020, Adding 3wt% of magnesium oxide nanoparticles to the denture soft liner provided better antimicrobial activity than the control group. It significantly suppressed the growth of candida albicans and Staphylococcus aureus for up to six months (Abdel-Rahman, 2020).

In 2021, Copper Oxide Nanoparticles were added successfully to the soft denture liner. Incorporating Copper Oxide Nanoparticles at a concentration of 500µgmL into the soft denture liners exhibited significant activity in inhibiting candida albicans (Ansarifard *et al.*, 2021).

In 2022, a study aimed to determine how adding silicon dioxide nanoparticles to soft-lining materials affects Candida albicans adhesion, contact angle, and surface roughness. The result of adding 0.25% and 0.5% of silicon dioxide nanoparticles to the acrylic soft liner shows a decrease in candida albicans' adhesion, contact angle, and surface roughness (Gad *et al.*, 2022).

In 2022, Adding 1% and 1.5% by weight of Barium titanate nanoparticles into the soft liner improved the antifungal activity of the soft denture liner, while surface hardness did not significantly change (Abdulbaqi, 2022).

In 2022, 2% w/w silver zinc zeolite nanoparticles were incorporated in a soft denture liner to investigate the antifungal properties and showed a superior effect on all tested groups (Ferreira *et al.*, 2022).

In 2023, The result of the addition of 1.0 wt.%, 1.5 wt.%, and 2 wt.% titanium oxide nanoparticles into a heat-cured soft denture liner showed antifungal activity observed by the reduction of candida albicans colonization. When titanium oxide nanoparticles' concentration increased, the soft liner's anti-microbial activity also increased (Ahmed *et al.*, 2023).

3- Plant powder extract added to soft liner:

In 2018, a study aimed to investigate the effect of Aloe vera powder with concentrations of 3% and 10% incorporated with heat cure acrylic soft-lining material on the adherence of candida albicans, tear strength, and shear bond strength. This study's results indicated that both aloe vera concentrations showed a higher decrease in Candida albicans cell count compared to the control group, a non-significant difference in tear strength, and a significant increase in soft liner shear bond strength for the experimental groups (Abdulwahhab & Jassim, 2018).

In 2020, a study was conducted on Piper betle extract with varying concentrations from 0.25 to 20% w/w to investigate a short-term soft lining material's anti-candidal properties, surface hardness, and gelation time. A soft liner containing at least 5% w/w of Piper betle powder showed an inhibitory effect against candida albicans, and this concentration did not significantly alter the surface hardness and gelation time of soft lining material. A larger inhibition zone was calculated with increased concentration of Piper betle (Kumpanich *et al.*, 2020).

In 2020, grape seed extract was added to the soft lining material to assess the antifungal activity, tensile bond strength, and surface roughness. Both concentrations of grape seed 5% and 10% w/w exhibit a significant increase in antifungal activity and tensile bond strength, while the concentration 5% w/w showed a considerable increase in surface roughness (Aref, 2020).

In 2023, a study was conducted to compare the antifungal efficacy of soft liner incorporated with powder extract of Lawsonia inermis and Withania somnifera on candida albicans growth. The concentration of Lawsonia inermis and Withania somnifera powder extract was 1%, 3%, 5%, and 7% incorporated in the soft liner, and the inhibition zone against candida albicans was calculated to measure the antifungal properties. The result was that Lawsonia inermis and Withania somnifera natural herb extracts have been shown to have antifungal activity against candida albicans with all concentrations used of these natural plant powders (Jaiswal *et al.*, 2023).

References:

- Abdallah, R. M., & Aref, N. S. (2021). *Curcumin containing soft liner as an alternative treatment modality for oral candidiasis*. World Journal of Dentistry, 12(6), 435-440. doi:<https://doi.org/10.5005/jp-journals-10015-1867>

- Abdel-Rahman, H. K. (2020). *Effect of adding magnesium oxide nanoparticles on the antimicrobial activity of a denture soft liner*. Polytechnic Journal, 10(2), 20. doi:<https://doi.org/10.25156/ptj.v10n2y2020.pp132-137>
- Abdulbaqi, A. P. D. H. J. (2022). *THE VALUE OF BARIUM TITANATE NANO-PARTICLES INCORPORATION INTO SOFT DENTURE LINING MATERIAL ON CANDIDA ALBICANS ADHERENCE AND OTHER PROPERTIES*. University of Baghdad,
- Abdulwahhab, A. R., & Jassim, R. K. (2018). *The effect of aloe vera extract on adherence of candida albicans and other properties of heat cure denture soft lining material*. International Journal of Medical Research & Health Sciences, 7(3), 94-103.
- Ahmed, A. Q., Al-Hmedat, S. J. A.-Z., Hanweet, D. M., & Haider, J. (2023). *Assessing the antifungal activity of a soft denture liner loaded with titanium oxide nanoparticles (TiO₂ NPs)*. Dentistry Journal, 11(4), 90. doi:<https://doi.org/10.3390/dj11040090>
- Al-Rubaie, N. A., & Al-Khafaji, A. M. (2024). *Investigation of piranha solution on Color Stability of heat cure acrylic*. (Humanities, social and applied sciences) Misan Journal of Academic Studies, 23(51), 17-26. doi:<https://doi.org/10.54633/2333-023-051-002>
- Al-Sammraie, M. F., Fatalla, A. A., & Atarchi, Z. R. (2024). *Assessment of the correlation between the tensile and diametrical compression strengths of 3D-printed denture base resin reinforced with ZrO₂ nanoparticles*. Journal of Baghdad College of Dentistry, 36(1), 44-53. doi:<https://doi.org/10.26477/jbcd.v36i1.3590>
- Al-Shammari, S. S., Abdul-Ameer, F. M., Bairam, L. R., & Al-Salihi, Z. (2023). *The influence of lemongrass essential oil addition into heat cured acrylic resin against Candida albicans adhesion*. Journal of Baghdad College of Dentistry, 35(3), 67-75. doi:<https://doi.org/10.26477/jbcd.v35i3.3457>
- Alamen, B. M., & Naji, G. A.-H. (2018). *The effect of adding coconut oil on candida albicans activity and shear bond strength of acrylic based denture soft lining material*. J Res Med Dent Sci, 6(5), 310-318.
- Alfahdawi, I. (2018). *New Direct Resilient Relining Material of Denture Base*. International Medical Journal, 25(2), 125-127. doi:https://www.researchgate.net/publication/324017212_New_Direct_Resilient_Relining_Material_of_Denture_Base
- AlFuraiji, N. H., Altaie, S. F., & Qasim, S. S. (2024). *Evaluating the influence of Ti6Al4V alloy particles on mechanical properties of heat-cured PMMA*. Journal of Baghdad College of Dentistry, 36(2), 44-53. doi:<https://doi.org/10.26477/jbcd.v36i2.3676>
- Ansarifard, E., Zarehshahrabadi, Z., Sarafraz, N., & Zomorodian, K. (2021). *Evaluation of antimicrobial and antibiofilm activities of copper oxide nanoparticles within soft denture liners against oral pathogens*. Bioinorg. Chem. Appl., 2021(1), 9939275. doi:<https://doi.org/10.1155/2021/9939275>
- Aref, N. S. (2020). *An in-vitro assessment of surface roughness, tensile bond strength and antifungal activity of grape seed extract-modified softliner*. J. Contemp. Dent. Pract., 21(4), 353-358. doi:<https://doi.org/10.5005/jp-journals-10024-2810>

- Babu, K. A. S. (2019). *A Beginners guide for soft liners-Mini review*. Journal of Pharmaceutical Sciences and Research, 11(12), 3802-3805. doi:<https://doi.org/10.37506/v10/i12/2019/ijphrd/192401>
- Chauhan, M. S., Trivedi, R., Singh, P. R., Chopra, D., Sarkar, D., & Thodsare, H. S. (2021). *Assessment of the water sorption and hardness of silicone and acrylic-based soft liners at different time period: an in vitro study*. Int J Cur Res Rev, 13(05), 2. doi:<https://doi.org/10.31782/ijcrr.2021.sp153>
- Chladek, G., Mertas, A., Barszczewska-Rybarek, I., Nalewajek, T., Żmudzki, J., Król, W., & Łukaszczyk, J. (2011). *Antifungal activity of denture soft lining material modified by silver nanoparticles—a pilot study*. Int. J. Mol. Sci., 12(7), 4735-4744. doi:<https://doi.org/10.3390/ijms12074735>
- Chladek, G., Żmudzki, J., & Kasperski, J. (2014). *Long-term soft denture lining materials*. Materials, 7(8), 5816-5842. doi:<https://doi.org/10.3390/ma7085816>
- Deng, J., Ren, L., Pan, Y., Gao, H., & Meng, X. (2021). *Antifungal property of acrylic denture soft liner containing silver nanoparticles synthesized in situ*. J. Dent., 106, 103589. doi:<https://doi.org/10.1016/j.jdent.2021.103589>
- Dutta, A. a. S., Madhurima. (2022). *SOFT LINERS IN DENTISTRY-A REVIEW OF THE LITERATURE ON ITS PROPERTIES AND CURRENT CONCEPT*. Global Journal For Research Analysis, 11, 1-3. doi:https://www.researchgate.net/publication/374558317_SOFT_LINERS_IN_DENTISTRY-A_REVIEW_OF_THE_LITERATURE_ON_ITS_PROPERTIES_AND_CURRENT_CONCEPT
- Ferreira, A. N., D'Souza, K., Aras, M., Chitre, V., Parsekar, S., & Pinto, M. J. W. (2022). *Long term antifungal efficacy of silver-zinc zeolite nanoparticles incorporated in two soft denture liners-An in vitro assessment*. Dent. Res. J. (Isfahan), 19(1), 12. doi:<https://doi.org/10.4103/1735-3327.338775>
- Gad, M. M., Bahgat, H. A., Edrees, M. F., Alhumaidan, A., Khan, S. Q., & Ayad, N. M. (2022). *Antifungal activities and some surface characteristics of denture soft liners containing silicon dioxide nanoparticles*. Journal of International Society of Preventive and Community Dentistry, 12(1), 109-116. doi:https://doi.org/10.4103/jispcd.jispcd_286_21
- Jaiswal, R. S., Kanathila, H., & Uppin, R. C. (2023). *Comparative evaluation of antifungal efficacy and potency of soft liners incorporated with powder extracts of Lawsonia inermis and Withania somnifera on the growth of Candida albicans—An in vitro study*. Indian Journal of Health Sciences and Biomedical Research kleu, 16(1), 54-59. doi:https://doi.org/10.4103/kleuhsj.kleuhsj_36_22
- Kumpanich, J., Eiampongpaiboon, T., Kanchanasavita, W., Chitmongkolsuk, S., & Puripattanavong, J. (2020). *Effect of Piper betle extract on anti-candidal activity, gelation time, and surface hardness of a short-term soft lining material*. Dent. Mater. J., 39(6), 1016-1021. doi:<https://doi.org/10.4012/dmj.2019-314>
- McCabe, J. F., & Walls, A. W. (2008). *Applied dental materials*. 9th Edn. John Wiley & Sons, Oxford, UK; Pp:
- Mohammed, H., & Fatalla, A. A. (2020). *The effectiveness of chitosan nano-particles addition into soft denture lining material on Candida albicans adherence*. Pak J Med Health Sci, 14, 3.

- doi:https://www.researchgate.net/publication/346605377_The_effectiveness_of_chitosan_nano-particles_addition_into_soft_denture_lining_material_on_candida_albicans_adherence
- Muttagi, S., & Subramanya, J. K. (2017). *Effect of incorporating seed oils on the antifungal property, surface roughness, wettability, weight change, and glucose sorption of a soft liner*. J. Prosthet. Dent., 117(1), 178-185. doi:<https://doi.org/10.1016/j.prosdent.2016.05.010>
- Nallaswamy, D. (2017). *Textbook of prosthodontics*. 2nd Edn. JP Medical Ltd, New Delhi, India; Pp:
- Naser, H. J., & Abdul-Ameer, F. M. (2022). *Evaluating the effect of lemongrass essential oil addition on some properties of heat cure acrylic soft-lining material*. Medical Journal of Babylon, 19(4), 646-652. doi:https://doi.org/10.4103/mjbl.mjbl_188_22
- Naser, H. J., & Abdul-Ameer, F. M. H. (2023). *Plants Extract Oils and Their Antimicrobial Activity in Treatment of Denture Stomatitis: Lemongrass Essential Oil (A review of literature)*. (Humanities, social and applied sciences) Misan Journal of Academic Studies, 22(45), 360-371 E. doi:<https://www.misan-jas.com/index.php/ojs/article/view/432>
- Noori, Z. S., Al-Khafaji, A. M., & Dabaghi, F. (2023). *Effect of tea tree oil on candida adherence and surface roughness of heat cure acrylic resin*. Journal of Baghdad College of Dentistry, 35(4), 46-54. doi:<https://doi.org/10.26477/jbcd.v35i4.3513>
- Özkan, Y. K. (2017). *Complete Denture Prosthodontics: Planning and Decision-Making*. 1st Edn. Springer, Turkey; Pp:<https://doi.org/10.1007/978-3-319-69032-2>
- Pachava, K. R., Nadendla, L. K., Alluri, L. S. C., Tahseen, H., & Sajja, N. P. (2015). *Invitro antifungal evaluation of denture soft liner incorporated with tea tree oil: a new therapeutic approach towards denture stomatitis*. Journal of Clinical and Diagnostic Research: JCDR, 9(6), ZC62. doi:<https://doi.org/10.7860/jcdr/2015/12396.6132>
- Petrović, M., Kostić, M., Kostić, M., Krunic, N., Igić, M., Pešić, Z., & Otašević, S. (2014). *THERAPEUTIC ALTERNATIVES OF NATURAL COMPOUNDS IN TREATMENT OF CANDIDA-ASSOCIATED DENTURE STOMATITIS*. Acta Medica Medianae, 53(1). doi:<https://scindeks-clanci.ceon.rs/data/pdf/0365-4478/2014/0365-44781401073P.pdf>
- Rashid, A. A. L. (2021). *Evaluating the effect of artemisia aerial parts extracts on candida albicans growth and shear bond strength of soft denture liner*. Journal of Techniques, 3(2), 86-95. doi:<https://doi.org/10.51173/jt.v3i2.321>
- Songsang, N., Anunmana, C., Pudla, M., & Eiampongpaiboon, T. (2022). *Effects of litsea cubeba essential oil incorporated into denture soft lining materials*. Polymers, 14(16), 3261. doi:<https://doi.org/10.3390/polym14163261>
- Wadi, M. T. S., & Khalaf, B. S. (2024). *Adhesion of 3d printed acrylic resin with silicone soft liner after sandblast surface treatment (A Review of Literature)*. (Humanities, social and applied sciences) Misan Journal of Academic Studies, 23(51), 100_111-100_111. doi:<https://doi.org/10.54633/2333-023-051-009>
- Yasser, A. D., & Fatah, N. A. (2017). *The effect of addition of zirconium nano particles on antifungal activity and some properties of soft denture lining material*. Journal of baghdad college of dentistry, 29(4), 27-33. doi:<https://doi.org/10.12816/0042988>

Conflicts of Interest Statement

Manuscript title:

Soft denture liner and its additives

The authors whose names are listed immediately below certify that they have NO affiliations with or involvement in any organization or entity with any financial interest (such as honoraria; educational grants; participation in speakers' bureaus; membership, employment, consultancies, stock ownership, or other equity interest; and expert testimony or patent-licensing arrangements), or non-financial interest (such as personal or professional relationships, affiliations, knowledge or beliefs) in the subject matter or materials discussed in this manuscript.

Author names:

1. Ibrahim Ali Karam

2. Ghasak H. jani

The authors whose names are listed immediately below report the following details of affiliation or involvement in an organization or entity with a financial or non-financial interest in the subject matter or materials discussed in this manuscript. Please specify the nature of the conflict on a separate sheet of paper if the space below is inadequate.

Author names:


This statement is signed by all the authors to indicate agreement that the above information is true and correct (a photocopy of this form may be used if there are more than 10 authors):

Author's name (typed)

Author's signature

Date

Ibrahim Ali Karam

.....

13/2/2025

Ghasak H. jani

.....

13/2/2025