## **Baghdad Science Journal**

Volume 22 | Issue 5

Article 17

5-24-2025

# Theoretical Calculation of Radiation Shielding Properties of B<sub>2</sub>O<sub>3</sub>-Bi<sub>2</sub>O<sub>3</sub>-Al<sub>2</sub>O<sub>3</sub>-MgO Glasses Alloyed with MnO

Shlair Ibrahim Mohammed Department of Physiology, College of Medicine, University of Kirkuk, Kirkuk, Iraq, shleararyan@gmail.com

Zainab Qahtan Mosa Department of Physics, College of Education for Women, University of Kirkuk, Kirkuk, Iraq, Zainabqahtan@uokirkuk.edu.iq

Follow this and additional works at: https://bsj.uobaghdad.edu.iq/home

#### How to Cite this Article

Mohammed, Shlair Ibrahim and Mosa, Zainab Qahtan (2025) "Theoretical Calculation of Radiation Shielding Properties of B<sub>2</sub>O<sub>3</sub>-Bi<sub>2</sub>O<sub>3</sub>-Al<sub>2</sub>O<sub>3</sub>-MgO Glasses Alloyed with MnO," *Baghdad Science Journal*: Vol. 22: Iss. 5, Article 17. DOI: https://doi.org/10.21123/bsj.2024.10508

This Article is brought to you for free and open access by Baghdad Science Journal. It has been accepted for inclusion in Baghdad Science Journal by an authorized editor of Baghdad Science Journal.

**RESEARCH ARTICLE** 





# Theoretical Calculation of Radiation Shielding Properties of B<sub>2</sub>O<sub>3</sub>–Bi<sub>2</sub>O<sub>3</sub>–Al<sub>2</sub>O<sub>3</sub>–MgO Glasses Alloyed with MnO

### Shlair Ibrahim Mohammed<sup>® 1,\*</sup>, Zainab Qahtan Mosa<sup>® 2</sup>

<sup>1</sup> Department of Physiology, College of Medicine, University of Kirkuk, Kirkuk, Iraq

<sup>2</sup> Department of Physics, College of Education for Women, University of Kirkuk, Kirkuk, Iraq

#### ABSTRACT

The current work aims to calculate the gamma-ray shielding coefficients for six samples. The samples were  $65B_2O_3.20Bi_2O_3.10Al_2O_3$ . (5-x) MgO. xMnO ( $0 \le x \le 1 \mod \%$ ). prepared these samples by using the melt quenching method. The study measures MAC (mass attenuation coefficient) and linear attenuation coefficient ( $\mu_m$ ,  $\mu$ ). It also calculates the halve-value layer, ten-value layer (TVL), and mean free path (MFP). The calculation was conducted using the Phy-X/PSD and XCOM programs, in an energy range 1 keV–100 GeV. The study discusses comparing the results with each other showing a good agreement. The study has shown many results such as when the energy is higher than 10 MeV. There were many peaks in the low photon energy region (<0.1 MeV). The glass sample with the biggest MnO composition S6 shows many peaks at the M-, L-, and K-absorption photoelectric edges. The measured values that Phy-X/PSD and XCOM software produced showed good agreement. Also, there is a negative correlation between the HVL and material density. In addition, MFP and HVL values begin low and continuously increase as the incident energy of the photon rises to 5 MeV. Beyond 5 MeV, with energies, HVL and MFP dropped softly. Half-Value Layer values drop with the rise in the density and MnO contents.

**Keywords:** Protection properties, Glass, Photon attenuation-coefficient, Half value layer, Tenth value layer, XCOM, Phy-X/PSD

#### Introduction

Knowledge of shielding properties such as the coefficient of total linear-attenuation  $\mu$ , coefficient of mass attenuation ( $\mu_m = \mu/\rho$ ), mean free path (MFP), Tenth value layer (TVL), half value layer (HVL) and is essential in the domain of radiation physics.<sup>1–3</sup> shielding materials are used to control radiation exposure of Neutrons and gamma rays.<sup>4</sup> A radiation beam experiences attenuation when it enters a bodily part; the degree of attenuation varies with the medium's thickness and density.<sup>5</sup> Protective barriers and shields are used to reduce the dose of radiation exposure to people working in the field of radioactive sources.<sup>6</sup> Concrete and building materials are frequently employed as radiation protection materials due to their low cost and flexibility to be molded to any mason design.<sup>7,8</sup> However, concrete has various restrictions, including the addition of humidity content, being opaque to losing water, visible light, and incisions development.<sup>9</sup> Because of these constraints, a stronger shielding material is required. Glass is a better radiation shielding material than concrete.<sup>7,10</sup> Heavy metal oxide-containing glasses, such as Bi<sub>2</sub>O<sub>3</sub> and PbO, may significantly absorb gamma-ray and are one of the conceivable substitutes for concrete.<sup>11,12</sup> The authors have selected bismuth oxide as the material for preparing

\* Corresponding author.

E-mail addresses: shleararyan@gmail.com (S. I. Mohammed), Zainab-qahtan@uokirkuk.edu.iq (Z. Q. Mosa).

https://doi.org/10.21123/bsj.2024.10508

Received 26 December 2023; revised 5 April 2024; accepted 7 April 2024. Available online 24 May 2025

<sup>2411-7986/© 2025</sup> The Author(s). Published by College of Science for Women, University of Baghdad. This is an open-access article distributed under the terms of the Creative Commons Attribution 4.0 International License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Sample code	$B_2O_3$	$Bi_2O_3$	$Al_2O_3$	MgO	MnO	Density (g/cm <sup>3</sup> )
S1	65	20	10	5	0	4.900
S2	65	20	10	4.8	0.2	4.917
S3	65	20	10	4.6	0.4	4.928
S4	65	20	10	4.4	0.6	4.938
S5	65	20	10	4.2	0.8	4.961
S6	65	20	10	4	1	4.970

Table 1. The density and the chemical compositions of  $65B_2O_3.20Bi_2O_3.10Al_2O_3.(5-x)MgO.xMnO$  ( $0 \le x \le 1$ ).

the shielding, Due to the toxic action of lead. Because of their greater density and refractive index values, bismuth borate glasses have sparked a lot of attention.<sup>13</sup> B<sub>2</sub>O<sub>3</sub> is a good glass mold in trigonal [BO<sub>3</sub>]/ tetrahedral [BO<sub>4</sub>] units On the other hand, Bi<sub>2</sub>O<sub>3</sub> is affiliated with the denomination of conditional glass makers. It behaves as a modifier at low concentrations and the former at high concentrations.<sup>14</sup> In this study, We employed the software Phy-X/PSD to examine the photon protection characteristics of gamma for systems of  $65B_2O_3.20Bi_2O_3.10Al_2O_3.(5-x)MgO.xMnO$  glass.<sup>15</sup>

#### Materials and methods

The 65B<sub>2</sub>O<sub>3</sub>.20Bi<sub>2</sub>O<sub>3</sub>.10Al<sub>2</sub>O<sub>3</sub>.(5-x)MgO. xMnO glasses' chemical composition, concentration, and densities were acquired,<sup>15</sup> which is six samples of glass like those described in Table 1. which shows that as the concentration of the MgO decreases from 5 to 4 mol% the MnO concentration increases from 0 to 1 mol%. The software Phy-X/PSD enhanced by Şakar et al. is able to be utilized as open-source code and online. Phy-X/PSD program was created with the runtime environment Node.js v8.4.0Nginx 1.15.8 enhance security between the server and the client browser. The communication between the server and client browsers is secured using Positive SSL 256-bit encryption. It can calculate numerous shielding factors at various energies.<sup>16</sup> The Phy-X/PSD system rapidly and precisely evaluates the attenuation parameters, allowing the user to store the estimated values in an Excel dossier conveniently. The computations are broken down into three stages: (i) Materials definition: the weight fraction, sample density, and mole fraction are all entered. (ii) The energies are chosen from two specified ranges: 1 keV to 100 GeV and 15 keV to 15 MeV. In Phy-X/PSD, there are other readily accessible radioactive sources and energies that are widely recognized. (iii) Setting the properties: 18 protection properties can be counted, including  $\mu$ ,  $\mu_m$ , TVL, MFP, and HVL.<sup>15</sup> XCOM is a mixed rule-based software or dataset. It may provide mass coefficient attenuation for various elements within a specific energy range from 1 keV to 100 GeV

for various interaction processes such as coherent and incoherent scattering, pair production, and photoelectric-absorption. Generally, the Lambert-Beer rule describes the coefficient of mass-attenuation of the samples as shown in Eq. (1).<sup>17</sup>

$$\mu_m = \sum_{i=1}^n w_i \mu_m = \frac{\mu}{\rho} \tag{1}$$

Where  $w_i$  and  $\mu_m$  are, respectively, the fraction by weight of  $i^{th}$  of n elements contained in the glass and the mass attenuation coefficient.

The mean free-path (MFP) denotes the average traveled distance that a photon travels before undergoing a collision. The half-value layer (HVL) refers to the thickness of a substance at which 50% of the intensity of a photon incident has been reduced. HVL and MFP can be explained as:  $^{18-20}$ 

$$MFP = \left(\frac{1}{\mu}\right) \tag{2}$$

$$HVL = \frac{0.693}{\mu} \tag{3}$$

Here,  $\mu$  represents the linear-attenuation coefficient (LAC).

#### **Results and discussion**

The study has calculated many features such as the coefficient of linear attenuation (LAC), coefficient of mass attenuation (MAC), MFP, HVL, and TVL by the use of the XCOM and Phy-X/PSD programs. XCOM and Phy-x programs were used to measure the MAC (mass attenuation-coefficient). MAC coefficient of mass attenuation drops continuously with an energy photon, the Phy-X/PSD software and XCOM values for a specific sample in the range of energy 1 keV to 100 GeV showed that there was a negative correlation between the photon energies and the mass attenuation and linear attenuation of the glass samples. This is because higher energy photons have a greater tendency to interact with the electrons in the material, causing electron emission and



Fig. 1. The Phy-X/PSD program provides the  $\mu_m$  mass-attenuation coefficient values for calculated data samples.

the formation of defects.<sup>21</sup> This arises from when the radiation interacts with matter and energy.<sup>22</sup> The photon interacts with matter in three ways: the photoelectric effect at low energies (less than 100 keV), pair production at high energies (above  $10^6$  keV), and Compton scattering occurs at medium energies (between  $10^2-10^6$  keV). The MAC values are calculated by the Phy-X/PSD software as in Fig. 1.

Then, they quickly dropped to a depressed energy range of 1 keV < E < 100 keV, the value is biggest if the energy becomes higher than 100 keV owing to the K-absorption brim of element (MnO). All  $\mu_m$ sample values are in the range of 1 to 0.06 cm<sup>2</sup>.g<sup>-1</sup>, So, in a low-energy region, the MAC value drops quickly, if the scattering Compton dominates. When the energy is higher than 10 MeV, There were many peaks at low photon energy region (<0.1 MeV). This work examines the MnO concentricity trace on the shielding features of 65B<sub>2</sub>O<sub>3</sub>.20Bi<sub>2</sub>O<sub>3</sub>.10Al<sub>2</sub>O<sub>3</sub>. (5-x) MgO.xMnO system of glass. The total MAC, from the calculation, is seen as the MnO% concentration function in Figs. 1 and 2.

Increasing the MnO concentration raises the mass attenuation coefficient showing that  $\mu_{\rm m}$  of  $65B_2O_3.20Bi_2O_3.10Al_2O_3$ . (5-x) MgO. xMnO system was 0.0982 cm<sup>2</sup>.g<sup>-1</sup> and decreased to 0.098 cm<sup>2</sup>.g<sup>-1</sup> at 511 keV for radioactive source as seen in (Table 2)<sup>22</sup> Na, and at <sup>137</sup>Cs from 0.098224 cm<sup>2</sup>.g<sup>-1</sup> to 0.098221 cm<sup>2</sup>.g<sup>-1</sup> at 662 keV as the MgO concentration decrease.<sup>23</sup> A study very well confirmed the measured values that Phy-X/PSD and XCOM software produced. The current work examined the MnO concentration impact on the shielding features of the 65B<sub>2</sub>O<sub>3</sub>.20Bi<sub>2</sub>O<sub>3</sub>.10Al<sub>2</sub>O<sub>3</sub>. (5-x)MgO.xMnO glass system.



Fig. 2. The XCOM software values of  $\mu_m$  the total mass-attenuation coefficient estimated glass samples.



Fig. 3. Phy-X/PSD Software values of the linear-attenuation ( $\mu$ ) for the samples of glass.

Figs. 1 to 4, shows the calculated  $\mu$ m &  $\mu$  values as a function of MnO% concentration. Also, the mass & linear attenuation coefficients positively correlate with the MnO concentration and the 65B<sub>2</sub>O<sub>3</sub>.20Bi<sub>2</sub>O<sub>3</sub>.10Al<sub>2</sub>O<sub>3</sub>. (5-x) MgO.xMnO glass system rises with the rise of the density of the material.<sup>24</sup> Eq. (1) shows the inverse relation between MAC and density.

An (HVL) half Value-Layer of the checked samples ranges between 1 keV and 100 GeV. In contrast, there was a negative correlation between the MnO concentration and the HVL. Eq. (3) shows that there is an inverse link between HVL and the LAC, as illustrated in Figs. 5 and 6. HVL increases gradually as the input photon energy increases for a range of energies.<sup>25</sup> The HVL of the glasses S1 increased from 0.022063584 to 0.045658202 cm, while it increased

Table 2. The mass attenuation coefficient of  $65B_2O_3$ . $20Bi_2O_3$ . $10Al_2O_3$ .(5-x)MgO.xMnO ( $0 \le x \le 1$ ).

511 keV 511 keV 662 keV 662 keV Energy Sample code Phy-x/PSD XCOM Phy-x/PSD XCOM **S**1 0.0982204 0.09822 0.0822686 0.08224 S2 0.098213 0.09821 0.08226088 0.08224 S3 0.0982056 0.09821 0.08225315 0.08223 S4 0.0981982 0.0982 0.08224543 0.08222 S5 0.0981908 0.09819 0.08223771 0.08221 S6 0.0981834 0.09818 0.08222999 0.08221



Fig. 4. The XCOM program values of the linear-attenuation ( $\mu$ ) for the glass samples.



Fig. 5. The half-value layer of the selected samples with the energy of a photon, calculated by Phy-X/PSD.

from 0.021764941 to 0.044812375 cm for S6 at photon energies (1–100 MeV). A study shows that the HVL readings of the last sample (S6) were smaller values because of the MnO concentration. Also, there is a negative correlation between the HVL and material density. Figs. 5 to 8, depict the computed mean free path (MFP) and HVL values for the glass samples with



Fig. 6. The half-value layer of the selected samples with the energy of a photon, calculated by the XCOM program.



**Fig. 7.** Shows the mean free path (MFP) of the chosen samples using the Phy-X/PSD program.

a range of 1 keV to 100 GeV of energies. In addition, it has been discovered that the MFP and HVL values start low and progressively rise as the incident photon energy increases up to 5 MeV. Beyond 5 MeV, reaching these energies, HVL and MFP dropped slightly, the rate at which MFP and HVL are decreasing is sluggish



Fig. 8. The XCOM program was used to determine the variation of the (MFP) of the selected samples.



Fig. 9. Tenth-value layers of the chosen samples measured by Phy-X/PSD.

as incident energy increase. Half-Value Layer values drop with the rise in the density and MnO contents as obtained in Ref.<sup>26</sup> The photon-matter interaction mechanisms outlined for the  $(\mu/\rho = \mu_m)$  can be referred to as the current HVL behavior for these glass samples.

When higher than 5 MeV, the drop in the HVL and MFP is slight with the incident energy. Also, there is a clear rise in the MnO concentration and density decreasing HVL and MFP values. Furthermore, the sample S6 absorption edges are lower than those of the other samples. TVL (tenth-value layer) values calculated for the glass investigated samples by XCOM and Phy-x at the range (1 keV–100 GeV) are clarified in Figs. 9 and 10. The values of TVL were found



Fig. 10. Tenth-value layers of the chosen samples measured by XCOM.

low initially and with the increase in energy incident photons gradually increased. Where the sample edge S1 was found greater than the first edge of S6.<sup>23</sup> Good agreements between the calculated values.

#### Conclusion

Some of the gamma-ray attenuation parameters were calculated for glass samples with a gamma energy range of 1 kev-100 Gev utilizing the Phy-X/PSD and XCOM programs. It was found that the mass-attenuation coefficient (MAC) and the linear-attenuation coefficient (LAC) concentrations increased as MgO and MnO decreased and increased respectively.<sup>24</sup> However, the HVL and MFP, both rise as the amount of MnO increases and the amount of MgO decreases. It was found that the values of MAC and LAC tend to fall as the photon energy increases, whilst halve-value layer, ten-value layer (TVL) and mean free path (MFP) increase. Due to lower HVL values (1.065\*10<sup>-6</sup>-0.05 cm) and values of MFP, the S6 glass system demonstrates superior protective capacity compared to the other glass samples in 65B2O3-20Bi2O3-10Al2O3-(5-x)MgO-xMnO systems  $(1.54*10^{-6}-0.07 \text{ cm})$ . While the mass-attenuation coefficient is at its highest for the S6 sample which contains 4 (mol%) MgO and 1 (mol%) MnO, the (MAC) values for S6 glass range from 130922.6091-2.71 cm<sup>2</sup>.g<sup>-1</sup>, and the gamma rays' energy varies from 1 keV to 100 GeV. The S6 specimen of top density offers better photon protection capabilities due to its low values of TVL (tenth-value layer), (half-value layer) HVL, and MFP (mean free path), as well as its high LAC (coefficient of linear-attenuation) and MAC (coefficient of mass attenuation) values. All values of  $\mu_{Phy-x}$  are slightly greater than the  $\mu_{XCOM}$  values. The mass-attenuation values obtained from both methods confirmed the accuracy of the current Phy-X/PSD. The study proved that the sixth sample provides the best protection against gamma rays, so it can be used to protect against radiation. It was calculated in two ways to further confirm that it can be used in  $\gamma$ -ray shielding.

#### **Authors' declaration**

- Conflicts of Interest: None.
- We hereby confirm that all the Figures and Tables in the manuscript are ours. Furthermore, any Figures and images, that are not ours, have been included with the necessary permission for republication, which is attached to the manuscript.
- No animal studies are present in the manuscript.
- No human studies are present in the manuscript.
- Ethical Clearance: The project was approved by the local ethical committee at University of Kirkuk.

#### Authors' contribution statement

This work was carried out in collaboration between all authors. Sh. I. M. collected the samples and wrote and edited the manuscript with revisions ideas. Z. Q. M., analysis of the data with revision idea.

#### References

- Sukhpal S, Ashok K, Devinder S, Kulwant ST, Gurmel S. Barium – borate – flyash glasses: as radiation shielding materials. Nucl Inst Methods Phys Res. 2008;266:140–146. https://doi. org/10.1016/j.nimb.2007.10.018.
- Sayyed MI. Bismuth modified shielding properties of zinc boro-tellurite glasses. J Alloys Compd. 2016;688:111–117. https://doi.org/10.1016/j.jallcom.2016.07.153.
- Sayyed MI. Investigation of shielding parameters for smart polymers. Chin J Phys. 2016;54(3):408–415. https://doi.org/ 10.1016/j.cjph.2016.05.002.
- Vishwanath PS, Badiger NM, Kaewkhao J. Radiation shielding competence of silicate and borate heavy metal oxide glasses: comparative study. J Non-Cryst Solids. 2014;404:167–173. https://doi.org/10.1016/j.jnoncrysol.2014.08.003.
- Shafik SS, Basim KR, Rajiha RM, Wijdan TF. Study the Shielding Properties against Gamma-rays for Epoxy Resin Reinforced by Different materials. Baghdad Sci J. 2011;8(3):705– 710. https://doi.org/10.21123/bsj.2011.8.3.705-710.
- Samer KY, Laith Abd, Al-Aziz A. Impact of geometric factor in accumulation factor measurements of gamma rays. Baghdad Sci J. 2021;2(4):6–623. https://doi.org/10.21123/bsj.2005. 659.

- Kaundal RS, Sandeep K, Narveer S, Singh KJ. Investigation of structural properties of lead strontium borate glasses for gamma ray shielding applications. J Phys Chem Solids. 2010;71(9):1191–1195. https://doi.org/10.1016/j.jpcs.2010. 04.016.
- Mostafa AM, Shams AM, Sayyed MI. Gamma ray shielding properties of PbO-B<sub>2</sub>O<sub>3</sub>-P<sub>2</sub>O<sub>5</sub> doped with WO<sub>3</sub>. J Alloys Compd. 2017;708:294–300. https://doi.org/10.1016/j. jallcom.2017.02.303.
- Sandeep K, Singh KJ. Investigation of lead borate glasses doped with aluminum oxide as gamma ray shielding materials. Ann Nucl Energy. 2014;63:350–354. https://doi.org/10. 1016/j.anucene.2013.08.012.
- Tuscharoen S, Kaewkhao J, Limkitjaroenporn P, Limsuwan P, Chewpraditkul W. Improvement of BaO: B<sub>2</sub>O<sub>3</sub>: fly ash glasses: radiation shielding, physical and optical Properties. Ann Nucl Energy. 2012;49:109–113. https://doi.org/10.1016/j.anucene.2012.05.017.
- Singh K, Singh N, Kaundal R, Singh K. Gamma-ray shielding and structural properties of PbO-SiO<sub>2</sub> glasses, Nucl Instrum Methods Phys Res B. 2008;266(6):944–948. https://doi.org/ 10.1016/j.nimb.2008.02.004.
- Ashok K. Gamma ray shielding properties of PbO-Li<sub>2</sub>O-B<sub>2</sub>O<sub>3</sub> glasses. Radiat Phys Chem. 2017;136:50–53. https://doi.org/ 10.1016/j.radphyschem.2017.03.023.
- Isabella-Ioana O, Hartmut H, Klaus B. Optical properties of bismuth borate glasses, Opt Mater. 2004;26(3):235–237. https://doi.org/10.1016/j.optmat.2003.10.006.
- Thomas M. Review of Bi<sub>2</sub>O<sub>3</sub> based glasses for electronics and related applications. Int Mater Rev. 2013;58(1): 3–40. https: //doi.org/10.1179/1743280412Y.0000000010.
- Krishna GP, Yusub S, Ramesh BA, Sree NR, Aruna V. Electrical and spectroscopic characteristics of B<sub>2</sub>O<sub>3</sub>-Bi<sub>2</sub>O<sub>3</sub>-Al<sub>2</sub>O<sub>3</sub>-MgO glasses alloyed with MnO. J Phys Chem Solids. 2022;170:110957. https://doi.org/10.1016/j.jpcs.2022.110957.
- Şakar E, Özpolat OF, Alım B, Sayyed MI, Kurudirek M. Phy-X/PSD: Development of a user friendly online software for calculation of parameters relevant to radiation shielding and dosimetry. Radiat Phys Chem. 2020;166:108496. https://doi. org/10.1016/j.radphyschem.2019.108496.
- Ali HT, Qahtan AM, Gulalla AK. Study of the properties of soil in Kirkuk, Iraq. J Radiat Res Appl Sci. 2016;9:256–265. https://doi.org/10.1016/j.jrras.2016.02.006.
- Ali H Taqi, Abdulahdi M, Ghalib S, Mohammed I. Shielding properties of glass samples containing Li<sub>2</sub>O, K<sub>2</sub>O, Na<sub>2</sub>O, PbO and B<sub>2</sub>O<sub>3</sub> by Geant4, XCOM and Experimental Data. Jordan J Phys. 2022;15:331–341. https://doi.org/10.47011/15.4.1.
- Sayyed MI, El-Mallawany R. Shielding properties of (100-x) TeO<sub>2</sub>-(x) MO<sub>3</sub> glasses. Mater Chem Phys. 2017;201:50–56. https://doi.org/10.1016/j.matchemphys.2017.08.035.
- Dong NG, El-Mallawany R, Sayyed MI, Tekin HO. Shielding properties of 80TeO<sub>2</sub>-5TiO<sub>2</sub>-(15-x) WO<sub>3</sub>-xAnOm glasses using WinXCom and MCNP<sub>5</sub> code. Radiat Phys Chem. 2017;141:172-178. https://doi.org/10.1016/j.radphyschem. 2017.07.006.
- 21. Amani A, Al Huwayz M, Alrowaili ZA, Al-Buriahi MS. Radiation attenuation of SiO<sub>2</sub>–MgO glass system for shielding applications. J Radiat Res Appl Sci. 2023;16(4):100746. https: //doi.org/10.1016/j.jrras.2023.100746.
- 22. Amal A EL-Sawy, Madbouly AM. Comparative study of gamma radiation shielding parameters for different oxide glasses. Eur Acad Res. 2018;VI(2):824. https://doi.org/10.13140/RG.2.2. 13185.10089.

- Ali HT, Ali IS, Azeldeen HI. Electromagnetic-ray absorption using B<sub>2</sub>O<sub>3</sub>-PbO-Na<sub>2</sub>O glass mixtures as radiation protection shields. Arab J Nucl Sci Appl. 2021;25(1):53–61. http://dx. doi.org/10.21608/ajnsa.2021.74814.1469.
- Almisned G, Iskender A, Huseyin OT, Ismail Yuksek, İsmail Ekmekçi. Variation in gamma ray shielding properties of glasses with increasing boron oxide content. Radiochimica Acta. 2022;111(3):217–223. https://doi.org/10.1515/ract-2022-0108.
- Hanfi MY, Sayyed MI, Lacomme E, Akkurt I, Mahmoud KA. The influence of MgO on the radiation protection and mechanical properties of tellurite glasses. Nucl Eng Technol. 2021;53(2000):2010. https://doi.org/10.1016/ j.net.2020.12.012.
- Al-Hadethi Y, Sayyed MI, Tijani SA. Gamma radiation attenuation properties of tellurite glass: A comparative study. Nucl Eng Technol. 2019;51(8):2005–2012. https://doi.org/ 10.1016/j.net.2019.06.014.

# الحساب النظري لخصائص التدريع الإشعاعي للزجاج -Bi2O3-Bi2O3 الحساب النظري لخصائص التدريع الإشعاعي للزجاج -Bi2O3-Bi2O3-MgO

### شلیر ابراهیم محمد 1، زینب قحطان موسی<sup>2</sup>

<sup>1</sup> فرع الفسلجة ، الكلية الطب، الجامعة كركوك، كركوك، العراق.
<sup>2</sup>القسم الفيزياء، الكلية التربية للبنات، الجامعة كركوك، كركوك، العراق.

#### الخلاصة

 $65B_2O_3.20Bi_2O_3.10Al_2O_3. (5-x) MgO. xMnO$  يهدف العمل الحالي الى حساب معاملات التدريع أشعة جاما لسنة عينات. MgO. xMnO (.5-x) MgO. xMnO (.5-x) العينات,تم تحضير هذه العينات باستخدام طريقة ذوبان تبريد. تقيس الدراسة معاملات التوهين الكتلية والخطية ( $\mu_m$ ,  $\mu$ ). كما يقوم أيضًا بحساب طبقة القيمة النصفية، وطبقة القيمة العشرة (TVL)، ومتوسط المسار الحر (MFP). تم إجراء الحساب باستخدام برامج Phy-X/PSD وPhy-X/PSD، في نطاق طاقة VOGC (TVL)، وتناقش الدراسة النتائج المحسوبة مع المحسوبة مع والخطية ( $\mu_m$ ,  $\mu$ ). كما يقوم أيضًا بحساب طبقة القيمة النصفية، وطبقة القيمة العشرة (TVL)، ومتوسط المسار الحر (MFP). تم إجراء الحساب باستخدام برامج Phy-X/PSD وPhy-X/PSD، في نطاق طاقة VOGC (VL)، وتناقش الدراسة النتائج المحسوبة مع بعضها اللبعض وقد لوحظت أتفاق جيدا. وقد أظهرت الدراسة العديد من التائج مثل أنه عندما تكون الطاقة أعلى من 10 (.5-x) (VL)، بعضها اللبعض وقد لوحظت أتفاق جيدا. وقد أظهرت الدراسة العديد من التائج مثل أنه عندما تكون الطاقة أعلى من 10 (.5-x) 
الكلمات المفتاحية: خصائص الحماية، زجاج، معامل تو هين الفوتون، طبقة نصف القيمة، طبقة القيمة العاشرة، Phy-، XCOM، الكلمات المفتاحية. X/PSD.