

(Al-Mn)

/ /

(أستلم 2013 / 5 / 14 ؛ فُجِل 2013 / 10 / 7)

(Al-Mn) (NiO) (ZnO) (Al₂O₃)
 UCS-20 ³⁷Cs (0.662 keV)
 (Al-Mn)+NiO (Al-Mn)+ZnO (Al-Mn)+Al₂O₃ (Al-Mn) NaI(Tl)
 0.151 mm⁻¹ (Al-Mn)+ZnO (Al-Mn)+Al₂O₃ (Al-Mn) 0.251 mm⁻¹
 (Al-Mn)+NiO
 (Al-Mn)+ZnO (Al-Mn)+NiO

Using Gamma-Rays to Determine the Homogeneity of Alloy (Al-Mn) Grafted by some Oxides

Raad A. Rasool Ahmed K. Muhemeed Muhsun W. Albadrani
Department of Physics/ College of Education/ University of Mosul

ABSTRACT

This research includes preparing samples of composite materials by using casting sand and hand mixing to disperse particles oxides such as (Al₂O₃) and (ZnO and (NiO) in the substrate of bases alloy (Al-Mn). We also use a narrow collimated mono-energetic beam of gamma-rays emitted from the decay of ¹³⁷Cs (0.662 keV) and a gamma spectrometer UCS-20 connected with a NaI(Tl) detector to determine the homogeneity of the materials (Al-Mn), (Al-Mn)+Al₂O₃, (Al-Mn)+ZnO, (Al-Mn)+NiO. The homogeneity test was determined from the percentage variations between the transmitted energy, the intensity of gamma-rays, and the linear attenuation coefficient at seven positions for each sample and the percentage of the standard deviation. The linear attenuation coefficients for the above samples were determined, the highest average values obtained 0.251 mm⁻¹ for (Al-Mn)+ZnO and the lowest average values obtained 0.151 mm⁻¹ for (Al-Mn)+NiO. It can be seen from the present results that the materials (Al-Mn), (Al-Mn)+Al₂O₃, (Al-Mn)+ZnO have a good homogeneity as compared with

(Al-Mn)+NiO. The linear attenuation coefficient of (Al-Mn)+ZnO sample was higher than its values in some materials used as gamma-radiation protection shields.

Keywords: Gamma-rays, composite materials, linear attenuation coefficients, Homogeneity test.

(Lilley, 2001) (1987) (Krane, 1987) (1976)

(1976) (1976)

) (2005) ⁹⁰Sr

MCG (2006

²⁴¹Am ¹⁵²Eu ¹³⁷Cs (Mheemeed *et al.*, 2012)

NBR

UCS-20 ¹³⁷Cs

(Al-Mn) NaI(Tl)

(NiO) (ZnO) (Al₂O₃)

Mn (Al-Mn) (NiO) (ZnO) (Al₂O₃)

(2012) 1%

750°C 4% ()

0.005

(7.8-8.2) mm

.mm

(0.5 cm)

(10 cm)

UCS-20

(1)

2.5cm×3.8cm

NaI(Tl)

4 cm


6 cm

¹³⁷Cs


(1) 2 mm

(2) 9 mm

(2)



:1



:2

(x)

.FWHM

(F) FWHM

(p)

F'

Δ_F(%)

$$\Delta_F(\%) = \frac{F' - F}{F'} \times 100\% \dots\dots\dots (1)$$

: (Lilley, 2001) I

I₀

$$I = I_0 e^{-\mu x}$$

$$\dots\dots\dots (2)$$

μ :

I'

I

Δ_I(%)

$$\Delta_I(\%) = \frac{I' - I}{I'} \times 100\% \dots\dots\dots (3)$$

(2)

μ

μ'

μ

Δ_μ(%)

$$\Delta_\mu(\%) = \frac{\mu' - \mu}{\mu'} \times 100\% \dots\dots\dots (4)$$

()

Δ_μ(%) Δ_I(%) Δ_F(%)

$$\sigma(\mu) = \left[\frac{\sum (\mu_i - \bar{\mu})^2}{(N-1)} \right]^{0.5} \quad \text{..... (5)}$$

$$\Delta_{\mu}(\%) = \left(\frac{\sigma}{Ave} \right) \times 100 \quad \Delta_I(\%) = \left(\frac{\sigma}{Ave} \right) \times 100$$

(Al-Mn)+NiO	(Al-Mn)+ZnO	(Al-Mn)+Al ₂ O ₃	(Al-Mn)	μ	FWHM	I
0.6%	0.33%	0.24%	0.098%	0.15%	$\Delta_F(\%)$	$\Delta_I(\%)$

(Al-Mn)+ZnO	(Al-Mn)+Al ₂ O ₃	(Al-Mn)	$\mu(\%)$	$\Delta_I(\%)$
6.65%	0.02%	4.34%	0.77%	0.64%
4.4%	57.62%	0%	$\Delta_{\mu}(\%)$	

(Al-Mn)+ZnO	(Al-Mn)+Al ₂ O ₃	(Al-Mn)	$\mu(\%)$	$\Delta_I(\%)$
2.64 g/cm ³	2.23 g/cm ³	2.68 g/cm ³	2.66 g/cm ³	1%
				0.16%

(2012) (Al-Mn)+NiO NiO

0.151 mm⁻¹ 0.251 mm⁻¹

(Al-Mn)+NiO (Al-Mn)+ZnO
(5) .0.206 mm⁻¹

.662keV

Special lead (Mavi, 2012) Cappa Bonita μ (Al-Mn)+ZnO μ
(El-Taher, 2007) Diorite rock (El-Khayatt,2011) Concrete (white sand) (Fathi,2005) glass
(2000) Compressed soil

(Al-Mn)+ZnO (Al-Mn)+Al₂O₃ (Al-Mn) - 1
(Al-Mn)+NiO - 2
(Al-Mn)+ZnO (Al-Mn)+Al₂O₃ (Al-Mn) - 3
(Al-Mn)+NiO - 4
(Al-Mn)+ZnO - 4

I₀=4490

(Al-Mn)

:1

x=8.045 mm

P	I(count/300sec)	Δ _I (%)	FWHM(ch)	Δ _F (%)	μ(cm ⁻¹)	Δ _μ (%)
1	3744	-0.02	26.24	0.2	0.226	0
2	3766	-0.61	26.33	-0.15	0.219	3.09
3	3785	-1.12	26.32	-0.11	0.212	6.19
4	3706	0.99	26.29	0	0.239	-5.75
5	3713	0.81	26.34	-0.19	0.236	-4.42
6	3768	-0.66	26.28	0.04	0.218	3.54
7	3720	0.62	26.25	0.15	0.234	-3.54
Ave	3743	0	26.29	0	0.226	0
σ	30.87		0.039		0.010	
(σ/Ave)*100	0.8		0.15		4.4	

$I_0=4646$ $(Al-Mn)+Al_2O_3$

:2

 $x=8.225\text{mm}$

P	I(count/300sec)	$\Delta_I(\%)$	FWHM(ch)	$\Delta_F(\%)$	$\mu(\text{cm}^{-1})$	$\Delta_\mu(\%)$
1	3965	-0.32	24.36	0	0.193	2.03
2	3972	-0.5	24.41	-0.08	0.191	3.16
3	3921	0.78	24.43	-0.16	0.206	-4.57
4	3926	0.66	24.39	0	0.205	-4.06
5	3989	-0.93	24.42	-0.12	0.185	6.09
6	3957	-0.12	24.4	-0.04	0.195	1.02
7	3935	0.43	24.38	0.04	0.202	-2.54
Ave	3952	0	24.39	0	0.197	0
σ	25.46		0.024		0.008	
$(\sigma/\text{Ave}) * 100$	0.64		0.098		4.06	

 $I_0=4490$ $(Al-Mn)+ZnO$

:3

 $x=8.185\text{mm}$

P	I(count/300sec)	$\Delta_I(\%)$	FWHM(ch)	$\Delta_F(\%)$	$\mu(\text{cm}^{-1})$	$\Delta_\mu(\%)$
1	3649	0.18	25.42	0.43	0.254	-1.2
2	3688	-0.89	25.55	-0.08	0.240	4.38
3	3664	-0.23	25.58	-0.2	0.248	1.2
4	3642	0.37	25.53	0	0.256	-1.99
5	3617	1.06	25.55	-0.08	0.264	-5.18
6	3694	-1.01	25.61	-0.31	0.238	5.18
7	3635	0.56	25.5	0.12	0.258	-2.79
Ave	3655.6	0	25.53	0	0.251	0
σ	28.1		0.06		0.01	
$(\sigma/\text{Ave}) * 100$	0.77		0.24		3.98	

x=7.815 mm I₀= 4646


(Al-Mn)+NiO

:4


p	I(count/300sec)	$\Delta_I(\%)$	FWHM(ch)	$\Delta_F(\%)$	$\mu(\text{cm}^{-1})$	$\Delta_\mu(\%)$
1	3858	6.65	27.65	- 0.14	0.238	-57.62
2	4102	0.75	27.74	- 0.47	0.159	-5.3
3	4246	-2.73	27.55	0.22	0.115	23.84
4	4001	3.19	27.6	0.04	0.191	-26.49
5	4316	-4.42	27.45	0.58	0.094	37.75
6	4350	-5.25	27.63	- 0.07	0.084	44.37
7	4058	1.81	27.65	- 0.14	0.173	-14.57
Ave	4133	0	27.61	0	0.151	
σ	179.34		0.09		0.056	
$(\sigma/\text{Ave}) * 100$	4.34		0.33		37.1	

:5


	(cm ⁻¹)	
(Al-Mn)+ZnO	0.251	
Lead	1.08	(1993)
Sample 5	0.478	Mheemeed <i>et al.</i> , 2012
Barite concrete	0.251	Stankovic <i>et al.</i> , 2010
Cappa Bonita	0.234	Mavi, 2012
Special lead glass	0.233	Fathi, 2005
Concrete (white sand)	0.168	El-Khayatt, 2011
Diorite rock	0.15	Jameel <i>et al.</i> , 2010
Compressed soil	0.126	(2000)



Position



Position




Position

(Al-Mn)

 $\Delta_\mu(\%)$ $\Delta_I(\%)$ $\Delta_F(\%)$


:3

.....




Position

(Al-Mn)+Al₂O₃




Position

Δ_μ(%) Δ_I(%) Δ_F(%)




Position

:4




Position

(Al-Mn)+ZnO




Position

Δ_μ(%) Δ_I(%) Δ_F(%)




Position

:5




Position

(Al-Mn)+NiO



Position

Δ_μ(%) Δ_I(%) Δ_F(%)



Position

:6

.37 (1993)
 .95 (1976)
 .(Al-Mn) (1976)
 (2012)
 (2005)
 .121-115 (1)16 (2006)
 110-103 (1)17
 (2000)
 .52-46 (2)2 (1987)
 70

- El-Taher, A. (2007). Comparative study of attenuation and scattering of gamma-rays through two intermediate rocks. *Indian J. Pure Appl. Phys.*, **45**, 198–203
- Fathi, F. (2005). Mass attenuation of gamma photons in special lead glass that can be used in radiation shielding windows. *Raf. J. Sci.*, **17**(2),130–138
- Jameel, H.; Al-dayel, O.; Al-horayess, O.; Al-ajyan, T. (2010). Gamma ray shielding from white sand. *Energy Power Eng.* **2**(1), 6–9. <http://www.scirp.org/journal/epe>
- Krane, K. (1987). "Introductory Nuclear Physics". Wiley, New York. Johns and Cunningham The Physics of Radiology, 3rd ed.
- Lilley, J. (2001). "Nuclear Physics Principles and Application". Wiley, University of Manchester, New York.
- Mavi, B. (2012). Experimental investigation of γ -ray attenuation coefficients for granites. *Annals of Nuclear Energy.* **44**, 22-25.
- Mheemeed, A.K.; Hasan, I.H.; Al-Jomaily, F.M. (2012). Gamma-ray absorption using rubber-lead mixtures as radiation protection shields. *J. Radioanal. Nucl. Chem.* **291**, 653–659
- Stankovic, S.; Ilic, R.; Jankovic, K.; Bojovic, D.; Loncar, B. (2010). Gamma radiation absorption characteristics of concrete with compound type materials. *Acta. Phys. Polonica. A.*, **117**(5), 812–816.