

وزارة
التعليم العالي والبحث العلمي
جامعة ميسان
كلية التربية الاساسية



مجلة ميسان للدراستات الأكاديمية للعوم الانسانية والاجتماعية والتطبيقية

Misan Journal For Academic Studies
Humanits, Social and applied Sciences

ISSN (PRINT) 1994-697X

(Online)-2706-722X

ايلول 2025

العدد 55

المجلد 24

2025 Sep

55 Issue

24 vol

مجلة ميسان للدراسات الأكاديمية

Misan Journal

Misan Journal

مجلة ميسان للدراسات الأكاديمية
العلوم الانسانية والاجتماعية والنظيقية
كلية التربية الاساسية/جامعة ميسان

ايلول 2025

العدد 55

المجلد 24

Sep 2025

Issue55

Vol24



مؤسسة الاستشهاد المرجعي وزمد
العلم والتكنولوجيا في العالم الإسلامي



مرفق الايداع في المكتبة الوطنية العراقية 1326 لسنة 2009

journal.m.academy@uomisan.edu.iq
<https://www.misan-jas.com/index.php/ojs>

الصفحة	فهرس البحوث	ت
1 - 13	Estimate of cold plasma on antibiotic resistance and biofilm formation in Staphylococcus aureus isolated from clinical cases Zainab Sabah Fahim Majid Kadhim Aboud Al Shibly	1
14 - 23	The Subjugation of Bodies, Gender, and Biopolitics in Nawal El Saadawi's Woman at Point Zero Ali Mohammed Hasan	2
24 - 33	A Comparative study between Boundary and Finite Element Techniques for solving Inverse Problems Farah A.Saeed Sarah F. Ghafel	3
34 - 47	Postcolonial Feminism and Political Injustice in Huda Barakat's The Tiller of Waters Afrah Abdul Jabbar AbdulSahib	4
48 - 60	Cordia Myxa Fruit Effect on Bacterial Adhesion to Heat-Cured Acrylic Denture Bases Noor R. Taha Shorouq M. Abass	5
61 - 74	Prevalence and detection of Yersinia enterocolitica isolated from different clinical cases Baneen Maan Kareem Hadaf Mahdi Kadhim	6
75 - 81	Molecular investigation of biofilm genes in Staphylococcus epidermidis Lamyaa Jabbar Abosaooda Baheejah Abees Hmood Al-Khalidi	7
82 - 101	Salivary Thiocyanate Levels and Buccal Mucosal Cells Changes in E-cigarette Users and Traditional Smokers Mufeed Muhammad Jawad Yas, Layla Sabri	8
102 - 142	The Metaphorical Representation of Coronavirus in Iraqi Newspaper Cartoons Hayder Tuama Jasim Al-Saedi	9
143 - 151	The Narrative Synthesis of Human Frailty and the Social Attributes of the Singaporean Society in Philip Jeyaretnam's Abraham's Promise" Rana Ali Mhoodar	10
152 - 161	Development of Thiadiazole and Schiff Base Derivatives: Synthesis, Spectral Characterization, and Antibacterial Activity Assessment Doha kareem Hussien Rafid Kais Kmal Haitham Kadhim Dakheel	11
162-172	Translating voices from the Tigris: The American Granddaughter as a case study Falah Hussein Hanoon Al-Sari	12
173 - 186	Synthesis and Characterization of Conductive Copolymer/MWCNT Nanocomposite via Chemical and Interfacial Polymerization Hajer A. Hussein Mohammed Q Mohammed	13
187 - 205	Synthesis, diagnosis, and study of the electrical properties of some new iron-polymer complexes containing Schiff bases and study of their thermal stability Abduljaleel Muhammad Abduljaleel Nadia Ashour Hussein Jassim Mohammed Saleh	14

206 - 221	Reptition in Surah Ghafir, Fussilt, and Ash-shura An - Applied Study Qusay Tawfiq Hantoush	15
222 - 233	The short story in the literature of Said Hashosh, with 'The White Rainbow' as a model. Rabab Hussain Muneer	16
234 - 249	Aesthetic functions in men's fabric and fashion designs Asaad Ati Halil Saad Al-Moussawi	17
250 - 264	Techniques and Methods of Deviation in the Poetry of Kazem Al-Hajjaj and Mohammed Al-Khafaji Imad Hameed Nassrah Al-Musaedi Danesh Mohammadi Rakati Yusuf Nazari	18
265 - 279	Assimilation and Its Impact on Morphological Structure A Phonological and Morphological Study of Poetic Samples from Various Historical Periods Suad Abbas Sayyid	19
280 - 302	The Degree to Which Middle School Mathematics Teachers Possess Creative Teaching Skills Saif Karim Muslim	20
303 - 317	Plantinga's Epistemological Justification for General Beliefs Sajjad Saleh Shenyar Abbas Mahdavi Mostafa Farhoudi Mohammad Keyvanfar	21
318 - 333	The effect of the situation on leaving out the forgotten non-metaphorical object in the Holy Qur'an Yassin Taher Ayez	22
334 - 349	Ambiguities and Their Role in Constructing Stylistic Connotation: A Reading in Ahmed Zeki Abo Shadi's Alyanbu'a Poetry Rania Ali Munim	23
350 - 368	The reality of Primary School Teachers' Practice of Social Sciences to The Contemporary Professional Criteria Qasim Jaleel Zayir Al-Ghurabi Ramla Jabbar Khadhm Al-Saedi	24
369 - 383	Rhythm techniques in the poetry of Hasab Al-Sheikh Jaafar Mayyada AbduLameer ISmael	25
384 - 393	Youm AlHashir in Holy Quran: Surat Alansan as A Case Study Ali Howair Swailem	26
394 - 408	Criminal Policy for Addressing Crimes of Disclosure of Occupational Secrets and Violations of Messages and Telegrams (Comparative Study) Mustafa Shakir Hussein	27

ISSN (Print) 1994-697X
ISSN (Online) 2706-722X

DOI:

<https://doi.org/10.54633/2333-024-055-013>

Received: 16/June/2025

Accepted: 23/June/2025

Published online: 30/Sep/2025



MJAS: Humanities, Social and
Applied Sciences
Publishers

The university of Misan.
College of Basic Education This
article is an open access article
distributed under the terms and
conditions of the Creative
Commons Attribution

(CC BY NC ND 4.0)

<https://creativecommons.org/licenses/by-nc-nd/4.0/>

Synthesis and Characterization of Conductive Copolymer/MWCNT Nanocomposite via Chemical and Interfacial Polymerization

Hajer A. Hussein^{1*}, Mohammed Q Mohammed¹,

¹Department of Chemistry, College of Education for Pure Sciences,
Basrah University, Basrah, Iraq

Email : pgs.hajer.ali@uobasrah.edu.iq

<https://orcid.org/0009-0009-6351-1485>

Abstract:

Various monomers were employed to synthesize copolymers, followed by the fabrication of nanocomposites through the incorporation of 1% carboxyl-functionalized multi-walled carbon nanotubes (MWCNTs-COOH). These nanotubes were modified in the laboratory to enhance the interaction between the polymer matrix and the nanotubes. The nano-doping has led to improve the electrical and thermal performance of the product materials. The FTIR, XRD, TGA, SEM, and EDX were utilized to characterize composites, while electrical conductivity was measured using the pellet method. The results revealed that the incorporation of functionalized MWCNTs led to significant improvements in electrical conductivity, thermal stability, and morphological structure of the copolymer systems, highlighting their potential for advanced electronic and optoelectronic applications.

Keywords: Nanocomposites, Copolymers, Carbon Nanotubes (MWCNTs-COOH), Electrical Conductivity, pellet method

1.Introduction:

In recent decades, the technology of industrial materials has witnessed remarkable growth, with nanocomposites especially those integrating polymers and carbon nanotubes standing out as a key area of innovation. This is due to the unique combination of organic polymer flexibility with the exceptional characteristics of carbon nanotubes[1], such as high electrical conductivity, mechanical strength[2], and thermal stability[3]. One of the main challenges in producing efficient polymer-nanotube systems lies in enhancing the interfacial interaction between the two components. To improve dispersion and compatibility, carbon nanotubes are commonly functionalized through acid treatments that introduce reactive groups like carboxyls, promoting stronger bonding with polymer chains[4]. In this study, a series of copolymers were synthesized using two distinct techniques: chemical polymerization and interfacial polymerization. Multiwalled carbon nanotubes (MWCNTs), previously functionalized by acid treatment, were

incorporated to fabricate nanocomposite materials with improved electrical conductivity, thermal stability, and surface morphology. This work represents a step forward in the design of multifunctional materials suitable for advanced applications such as sensors, smart coatings, and flexible electronics.

2. Experimental Section:

2.1. Materials:

1,8-naphthalendiamine (Merck), Carbazole and Ammonium peroxydisulfate (BDH, England), 2-aminophenol, Indole (Aldrich), multiwall carbon nanotube (MWNT) with outer diameter of 10-30 nm, hydrochloric acid (HCl), Nitric acid (HNO₃), Perchloric Acid (HClO₄) and Sulfuric acid (H₂SO₄) are purchased from Sigma – Aldrich, 8-Hydroxy quinolin.

2.2. Instruments and measurement systems:

FT-IR Spectrometer, X-ray Diffraction Measurements, (Rigaku Ultima IV "Japan", Thermo gravimetric analysis TG(TG-50A Shimadzu, Japan) Scanning Electron Microscopy (SEM) (TESCAN mira3) "Japan", Energy Dispersive X-Ray (EDX), Keithley 2400 source meter was used to measure I-V Characteristics.

2.3 samples preparation:

2.3.1. Chemical Functionalization of Multi-walled Carbon Nanotubes:

The chemical oxidation of multi-walled carbon nanotubes (MWCNTs) was carried out using a mixture of sulfuric acid and nitric acid in a 3:1 volume ratio, specifically 90 mL of sulfuric acid and 30 mL of nitric acid. The acids were prepared as a solution to minimize structural damage to the nanotubes during treatment. After 30 minutes, 0.3 grams of MWCNTs were added to the acid mixture[5]. The resulting suspension was magnetically stirred for six hours at 50°C[6]. Following the reaction, the mixture was washed several times with distilled water using a centrifuge to remove residual acids. The final product was then dried at room temperature (30°C) for 12 hours[7].

2.3.2. poly (2-aminophenol and 8- Hydroxy quinolin):

The copolymer was synthesized by dissolving 1.1612 g (8 mmol) of 8-hydroxyquinoline in 30 mL of 0.8730 g (8 mmol) of 2-aminophenol was dissolved in 50 mL of perchloric acid-acidified water (containing 1 mL of HClO₄). The two monomer solutions were mixed together, followed by the gradual addition of the oxidizing agent prepared by dissolving 3.6512 g (16 mmol) of ammonium persulfate in 15 mL of deionized water. The oxidant was added dropwise using a dropping funnel. The reaction mixture was stirred continuously for 48 hours using a magnetic stirrer to ensure complete polymerization. After completion of the reaction, the mixture was filtered, thoroughly washed with deionized water, and dried at 50 °C. The resulting precipitate appeared as a dark brown solid with a melting point above 300 °C[8]. Figure (1) illustrates the proposed reaction pathway for the formation of the[9]




Figure 1: illustrates the reaction equation for the synthesis of the copolymer poly(2-aminophenol-co-8-hydroxyquinoline)

2.3.3. poly (1,8-naphthalendiamine and Indol):

The copolymer was synthesized via interfacial polymerization at room temperature. A solution of 0.158 g (1mmol) of 1,8-naphthalenediamine was prepared by dissolving it in 40 mL of dichloromethane. In a separate beaker, 0.234 g (2 mmol) of indole was dissolved in 40 mL of dichloromethane. The two monomer solutions were then mixed together in 80 mL of deionized water containing 5 mL of hydrochloric acid (HCl). This oxidizing mixture was added along the wall of the reaction vessel to initiate the polymerization. The reaction was left undisturbed for three days at room temperature to ensure complete polymerization. After the polymerization process, the reaction mixture was filtered, washed thoroughly with deionized water, and dried at 50 °C. The resulting precipitate appeared black in color and exhibited a melting point above 300 °C[10][11] .




Figure (2) illustrates the reaction equation for the synthesis of the copolymer poly(1,8-naphthalenediamine-co-indole).

2.3.4. Synthesis of poly, (2-aminophenol and 8-Hydroxy quinolin), (1,8-naphthalendiamine and Indol) Carboxylated CNT Nanocomposite:

Separately, 0.003 g of functionalized multi-walled carbon nanotubes (MWCNTs) was dispersed using an ultrasonic bath to ensure uniform dispersion. The dispersed nanotubes were then added to the polymer solution, and the mixture was stirred continuously for 24 hours to allow proper interaction and integration. The resulting Nanocomposite was subsequently dried at 50 °C.

3. Results and discussion:

3.1.1. FTIR Fourier Transform Infrared Spectroscopy:





Figure (3) shows the FTIR spectrum of carboxylated carbon nanotubes







Figure (4) FTIR spectrum of (A) the copolymer of 8-hydroxyquinoline and 2-aminophenol
(B) the copolymer of 8-hydroxyquinoline and 2-aminophenol with MWNTs-COOH






Figure (5) shows the FTIR spectra of (A) the copolymer of 1,8-naphthalene diamine and indole, and (B) the copolymer of 1,8-naphthalene diamine and indole combined with MWNTs-COOH

Figure (3) the peaks at 3435 cm^{-1} is attributed to the stretching vibration of acidic hydroxyl (-OH) groups. A band observed at 2975 cm^{-1} corresponds to aliphatic C-H stretching vibrations [169]. Additionally, the band at 1745 cm^{-1} is assigned to the stretching vibration of the carbonyl (C=O) group [1745] [12] [13]. Figure (4) shows absorption bands at $3435\text{--}3269\text{ cm}^{-1}$ due to -OH and -NH stretching, indicating strong hydrogen bonding [14]. The 3061 cm^{-1} peak corresponds to aromatic C-H , confirming aromatic structure retention. Peaks at $1606\text{--}1573\text{ cm}^{-1}$ are related to C=C and C=N stretching, while $1290\text{--}1317\text{ cm}^{-1}$ indicates C-N-C linkages. The 758 cm^{-1} band suggests out-of-plane C-H bending, supporting the presence of substituted benzene rings [9]. Figure (4B) shows a broad band at $3400\text{--}3000\text{ cm}^{-1}$, attributed to overlapping -NH , -OH , and -COOH stretching, indicating hydrogen bonding between the copolymer and MWCNTs. The 3067 cm^{-1} peak corresponds to aromatic C-H , and the distinct 1715 cm^{-1} band indicates C=O stretching from CNT surface carbonyls. Sharp peaks at 1609 and 1573 cm^{-1} are assigned to aromatic C=C stretching. Figure (5) shows a broad band at $\sim 3300\text{ cm}^{-1}$ due to -NH/-NH_2 stretching, indicating aromatic amines in the polymer. Peaks at 1618 and 1562 cm^{-1} confirm the presence of aromatic C=C and C=N , while the 1336 cm^{-1} band evidences C-N bond formation between indole and 1,8-naphthalenediamine [15] [16]. Figure (5B), confirms the retention of structural features of both the copolymer and CNT-COOH [17], with a slight N-H peak shift suggesting possible hydrogen bonding or $\pi\text{-}\pi$ interactions between the two components.

3.1.2. thermal analysis(TG)




Figure (6) presents the thermogravimetric analysis (TGA) of (A) the copolymer of 2-aminophenol and 8- hydroxyquinoline, and (B) the copolymer of 2-aminophenol and 8-hydroxyquinoline incorporating MWNTs-COOH




Figure (7) shows the thermogravimetric analysis (TGA) of (A) the copolymer of indole and 1,8-naphthalene diamine, and (B) the copolymer of 1,8-naphthalene diamine and indole combined with MWNTs-COOH

Figure (6) TGA analysis revealed that the copolymer of 2-aminophenol and 8-hydroxyquinoline undergoes multi-step degradation with a total weight loss of 70% at 600 °C. In contrast, the nanocomposite with MWCNTs-COOH showed improved thermal stability, with a reduced total weight loss of 48%, indicating enhanced resistance due to nanotube incorporation. Figure (7) presents TGA data for the indole/1,8-naphthalenediamine copolymer and its nanocompositewith MWCNTs-COOH. Both samples showed two-step weight loss. The copolymer exhibited an initial 3.7% loss (70–152 °C) due to moisture and oligomer removal,

followed by a major 75% loss (166–570 °C) attributed to decomposition of unreacted monomers and polymer chains. In contrast, the nanocomposite demonstrated enhanced thermal stability, with only 47% total weight loss. The delayed degradation and reduced loss are ascribed to the stabilizing interaction between the nanotubes and the polymer matrix.

3.1.3. X-ray diffraction patterns:

The XRD pattern of Figure (8), representing the copolymer of 2-aminophenol and 8-hydroxyquinoline, shows a main diffraction peak at $2\theta \approx 27.48^\circ$, along with weaker peaks at $2\theta \approx 24.64^\circ$ and 32.24° . These reflections suggest a semi-crystalline nature of the copolymers. In the nanocomposite, a distinct peak appears at $2\theta \approx 26.76^\circ$ [18], corresponding to multi-walled carbon nanotubes (MWCNTs). Additionally, variations in peak intensity are observed, indicating potential interactions between the polymer matrix and the nanostructures. Figure (9), The XRD pattern of the indole/1,8-naphthalenediamine copolymer reveals a semi-crystalline structure with a dominant peak at $2\theta = 27^\circ$, indicating a well-ordered crystalline arrangement. Secondary peaks at 21° , 24° , and 30° 2θ reflect minor crystalline domains. The use of interfacial polymerization promotes higher structural organization, explaining the observed crystallinity.




Figure (8) XRD 2-Amino phenol and 8-hydroxyquinoline : 2-Amino phenol and 8-hydroxyquinoline- MWNT-COOH




Figure (9) XRD1,8- Naphthalendiamine and indol : 1,8-naphthalendiamine and Indol- MWNT-COOH

3.1.4.SEM measurements:




Figure (10): SEM images of (A) carbon nanotubes, (B) copolymer of 2-aminophenol with 8-hydroxyquinoline and (C) copolymer of indole with 1,8-naphthalenediamine

Figure (10) SEM analysis confirmed that the nanotubes preserved their cylindrical morphology after $\text{HNO}_3/\text{H}_2\text{SO}_4$ acid treatment, with no evidence of structural damage. This indicates effective surface functionalization while maintaining mechanical integrity, highlighting their suitability for chemically modified applications[19][20]. SEM (B) images revealed that the copolymer of 2-aminophenol and 8-hydroxyquinoline forms irregular aggregates with porous regions, indicating a polymeric network. Upon incorporation of carbon nanotubes, clear interaction and entanglement with the copolymer matrix were observed. SEM (C) analysis of the poly(1,8-naphthalenediamine-co-indole) copolymer revealed dense aggregates with sharp, rod- or needle-like crystalline structures. Upon incorporation of carbon nanotubes, clear interaction with the copolymer matrix was observed.

3.1.5. Electrical properties:

The I-V measurements of the polymer discs and their nanocomposites (1% MWCNTs-COOH) showed that the nanocomposites exhibited linear ohmic behavior, while some pure polymers showed non-linear characteristics. The improved conductivity in nanocomposites is attributed to the presence of MWCNTs enhancing charge transport.




Figure (12): Current-voltage (I-V) characteristics of the copolymer (indole and 1,8-naphthalenediamine) (P51) and its nanocomposite with MWCNTs-COOH (N23).




figure (11): Current-voltage (I-V) characteristics of the copolymer (2-aminophenol and 8-hydroxyquinoline) (P46) and its nanocomposite with MWCNTs-

4. Conclusion:

In this study, nanocomposite materials were successfully prepared by incorporating multi-walled carbon nanotubes functionalized with carboxyl groups (MWCNTs-COOH) into various copolymer matrices. The results demonstrated significant improvements in electrical conductivity, thermal stability, and surface morphology. These enhancements confirm that the functionalized carbon nanotubes effectively reinforce the polymer systems, making them promising candidates for advanced electronic and optoelectronic applications. Future studies are

recommended to explore the effects of varying nanotube concentrations and to evaluate the performance of these materials under different environmental and operational conditions

Conflict of Interest:

The authors declare no conflict of interest.

Authors' Declaration

The authors hereby declare that the work presented in this article is original and that any liability for claims relating to the content of this article will be borne by them

References:

- [1] S. M. Aqeel *et al.*, "Polyvinylidene fluoride (PVDF)/polyacrylonitrile (PAN)/carbon nanotube nanocomposites for energy storage and conversion," *Adv. Compos. hybrid Mater.*, vol. 1, pp. 185–192, 2018. <https://doi.org/10.1007/s42114-017-0002-5>
- [2] M. M. Lakouraj, R. Norouzian, and M. Tavakoli, "Synthesis, Characterization, and Properties of Sulfonated CNT-Doped Poly (aniline-co-carbazole)-PVA Conductive Films," *Macromol. Mater. Eng.*, vol. 308, no. 7, p. 2200696, 2023. <https://doi.org/10.1002/mame.202200696>
- [3] F. G. Granados-Martínez *et al.*, "MWCNTs-polymer composites characterization through spectroscopies: FTIR and Raman," *MRS Adv.*, vol. 3, no. 63, pp. 3757–3762, 2018. <https://doi.org/10.1557/adv.2018.627>
- [4] L. Joshi, A. K. Singh, and R. Prakash, "Polyindole/carboxylated-multiwall carbon nanotube composites produced by in-situ and interfacial polymerization," *Mater. Chem. Phys.*, vol. 135, no. 1, pp. 80–87, 2012. <https://doi.org/10.1016/j.matchemphys.2012.04.026>
- [5] X. Hu, S. Zuo, and M. Yang, "High-yield preparation of ultrahigh-hydrophilicity MWCNTs by highly controllable oxidation with concentrated HNO₃/HClO₄ mixture," *Appl. Surf. Sci.*, vol. 626, p. 157200, 2023. <https://doi.org/10.1016/j.apsusc.2023.157200>
- [6] T. A. Saleh, "The influence of treatment temperature on the acidity of MWCNT oxidized by HNO₃ or a mixture of HNO₃/H₂SO₄," *Appl. Surf. Sci.*, vol. 257, no. 17, pp. 7746–7751, 2011. <https://doi.org/10.1016/j.apsusc.2011.04.020>
- [7] L. T. M. Hoa, "Characterization of multi-walled carbon nanotubes functionalized by a mixture of HNO₃/H₂SO₄," *Diam. Relat. Mater.*, vol. 89, pp. 43–51, 2018. <https://doi.org/10.1016/j.diamond.2018.08.008>
- [8] Y. F. KHOBRADE, "STUDIES ON THE CONDUCTING POLYMER OF 8-HYDROXY QUINOLINE". https://www.academia.edu/download/78203234/2_43_1628252073_1IJAPBC RDEC20211.pdf
- [9] F. Doğan, I. Kaya, and K. Temizkan, "Chemical oxidative synthesis and characterization of poly (8-hydroxyquinoline) particles," *J. Macromol. Sci. Part A*, vol. 51, no. 12, pp. 948–961, 2014. <https://doi.org/10.1080/10601325.2014.967081>
- [10] X. Zhang, R. Chan-Yu-King, A. Jose, and S. K. Manohar, "Nanofibers of polyaniline synthesized by interfacial polymerization," *Synth. Met.*, vol. 145, no. 1, pp. 23–29, 2004. <https://doi.org/10.1016/j.synthmet.2004.03.012>

- [11] B. Gupta and R. Prakash, "Interfacial polymerization of carbazole: Morphology controlled synthesis," *Synth. Met.*, vol. 160, no. 5–6, pp. 523–528, 2010. <https://doi.org/10.1016/j.synthmet.2009.11.014>
- [12] S. A. Wulandari, H. Widiyandari, and A. Subagio, "Synthesis and characterization carboxyl functionalized multi-walled carbon nanotubes (MWCNT-COOH) and NH₂ functionalized multi-walled carbon nanotubes (MWCNTNH₂)," in *Journal of physics: conference series*, IOP Publishing, 2018, p. 12005. [10.1088/1742-6596/1025/1/012005](https://doi.org/10.1088/1742-6596/1025/1/012005)
- [13] N. G. Sahoo *et al.*, "Functionalized carbon nanomaterials as nanocarriers for loading and delivery of a poorly water-soluble anticancer drug: a comparative study," *Chem. Commun.*, vol. 47, no. 18, pp. 5235–5237, 2011. <https://doi.org/10.1039/C1CC00075F>
- [14] G. Thenmozhi, P. Arockiasamy, and R. J. Santhi, "Isomers of poly aminophenol: chemical synthesis, characterization, and its corrosion protection aspect on mild steel in 1 M HCl," *Int. J. Electrochem.*, vol. 2014, no. 1, p. 961617, 2014. <https://doi.org/10.1155/2014/961617>
- [15] Z. Z. Hou and Q. H. Yang, "Porous poly (1-naphthylamine) synthesized by interfacial polymerization," in *Materials Science Forum*, Trans Tech Publ, 2015, pp. 319–322. <https://doi.org/10.4028/www.scientific.net/MSF.809-810.319>
- [16] S. An, T. Abdiryim, Y. Ding, and I. Nurulla, "A comparative study of the microemulsion and interfacial polymerization for polyindole," *Mater. Lett.*, vol. 62, no. 6–7, pp. 935–938, 2008. <https://doi.org/10.1016/j.matlet.2007.07.014>
- [17] S. Lefrant, M. Baibarac, and I. Baltog, "Raman and FTIR spectroscopy as valuable tools for the characterization of polymer and carbon nanotube based composites," *J. Mater. Chem.*, vol. 19, no. 32, pp. 5690–5704, 2009. <https://doi.org/10.1039/B821136A>
- [18] M. A. Salam and R. Burk, "Synthesis and characterization of multi-walled carbon nanotubes modified with octadecylamine and polyethylene glycol," *Arab. J. Chem.*, vol. 10, pp. S921–S927, 2017. <https://doi.org/10.1016/j.arabjc.2012.12.028>
- [19] S. Mallakpour and A. Nezamzadeh Ezhie, "Preparation of polystyrene/MWCNT-Valine composites: Investigation of optical, morphological, thermal, and electrical conductivity properties," *Polym. Adv. Technol.*, vol. 29, no. 3, pp. 1182–1190, 2018. <https://doi.org/10.1002/pat.4229>
- [20] P. Nie, C. Min, H.-J. Song, X. Chen, Z. Zhang, and K. Zhao, "Preparation and tribological properties of polyimide/carboxyl-functionalized multi-walled carbon nanotube nanocomposite films under seawater lubrication," *Tribol. Lett.*, vol. 58, pp. 1–12, 2015. <https://doi.org/10.1007/s11249-015-0476-7>

Conflicts of Interest Statement.....

Synthesis and Characterization of Conductive Copolymer/MWCNT Nanocomposite via Chemical and Interfacial Polymerization

The authors whose names are listed immediately below certify that they have NO affiliations with or involvement in any organization or entity with any financial interest (such as honoraria; educational grants; participation in speakers' bureaus; membership, employment, consultancies, stock ownership, or other equity interest; and expert testimony or patent-licensing arrangements), or non-financial interest (such as personal or professional relationships, affiliations, knowledge or beliefs) in the subject matter or materials discussed in this manuscript.

Author names:

1. Hajer A. Hussein, Department of Chemistry, College of Education for Pure Sciences, Basrah University, Basrah, Iraq
2. Mohammed Q. Mohammed, Department of Chemistry, College of Education for Pure Sciences, Basrah University, Basrah, Iraq

Author names:

This statement is signed by all the authors to indicate agreement that the above information is true and correct (a photocopy of this form may be used if there are more than 10 authors):

Author's name (typed)

Author's signature

Date

Hajer A. Hussein



25-6-2025

Mohammed Q. Mohammed



25-6-2025